SENTINEL HOLDING
INSTITUT

SHI PRODUCT PASSPORT

Find products. Certify buildings.

SHI Product Passport No.:

15206-10-1050

Aton-Sperrgrund

Product group: Primers

KNAUF

Knauf Gips KG
Am Bahnhof 7
97346 Iphofen

Product qualities:

- **SHI** Product Assessment 2024
- **QNG** Qualitätssiegel Nachhaltiges Gebäude
- **DGNB** NEW CONSTRUCTION 2023.2
- **DGNB** NEW CONSTRUCTION 2023
- **DGNB** NEW CONSTRUCTION 2018
- **BNB-BN** NEUBAU V2015
- **EU** TAXONOMY
- **BREEAM** DE NEUBAU 2018
- **LEED** v4.1 (outside US)

CERTIFIED SUSTAINABLE PRODUCT
SHI PRODUCT PASSPORT
SENTINEL HOLDING INSTITUT
www.sentinel-holding.eu

Köttner

Helmut Köttner
Scientific Director
Freiburg, 17 August 2026

SENTINEL HOLDING
INSTITUT

Product:
Aton-Sperrgrund

SHI Product Passport no.:
15206-10-1050

KNAUF

Contents

SHI Product Assessment 2024	1
QNG - Qualitätssiegel Nachhaltiges Gebäude	2
DGNB New Construction 2023.2	3
DGNB New Construction 2023	4
DGNB New Construction 2018	5
BNB-BN Neubau V2015	6
EU taxonomy	7
BREEAM DE Neubau 2018	8
LEED v4.1	9
Product labels	10
Legal notices	11
Technical data sheet/attachments	12

The SHI Database is the first and only database for construction products whose comprehensive processes and data accuracy are regularly verified by the independent auditing company SGS-TÜV Saar

SGS TÜV SAAR

SENTINEL HOLDING
INSTITUT

Product:
Aton-Sperrgrund

SHI Product Passport no.:
15206-10-1050

KNAUF

SHI Product Assessment 2024

Since 2008, Sentinel Holding Institut GmbH (SHI) has been establishing a unique standard for products that support healthy indoor air. Experts carry out independent product assessments based on clear and transparent criteria. In addition, the independent testing company SGS regularly audits the processes and data accuracy.

Criteria	Product category	Harmful substance limit	Assessment	Notice
SHI Product Assessment	Paints and coatings	TVOC ≤ 300 µg/m^3 Formaldehyd ≤ 24 µg/m^3	Indoor Air Quality Certified (Advisory Note)	Achtung, Produkt enthält Isothiazolinone zur Topfkonservierung
Valid untill: 04 August 2026				

SENTINEL HOLDING
INSTITUT

Product:
Aton-Sperrgrund

SHI Product Passport no.:
15206-10-1050

KNAUF

QNG - Qualitätssiegel Nachhaltiges Gebäude

The Qualitätssiegel Nachhaltiges Gebäude (Quality Seal for Sustainable Buildings), developed by the German Federal Ministry for Housing, Urban Development and Building (BMWSB), defines requirements for the ecological, socio-cultural, and economic quality of buildings. The Sentinel Holding Institut evaluates construction products in accordance with QNG requirements for certification and awards the QNG ready label. Compliance with the QNG standard is a prerequisite for eligibility for the KfW funding programme. For certain product groups, the QNG currently has no specific requirements defined. Although classified as not assessment-relevant, these products remain suitable for QNG-certified projects.

Criteria	Pos. / product group	Considered substances	QNG assessment
3.1.3 Schadstoffvermeidung in Baumaterialien	5.3 Coatings on mineral surfaces	VOC / emissions	QNG ready
Verification: Sicherheitsdatenblatt vom 07.06.2022			

SENTINEL HOLDING
INSTITUT

Product:
Aton-Sperrgrund

SHI Product Passport no.:
15206-10-1050

KNAUF

DGNB New Construction 2023.2

Criteria	No. / Relevant building components / construction materials / surfaces	Considered substances / aspects	Quality level
ENV 1.2 Local environmental impact			Not relevant for assessment

SENTINEL HOLDING
INSTITUT

Product:
Aton-Sperrgrund

SHI Product Passport no.:
15206-10-1050

KNAUF

DGNB New Construction 2023

The DGNB System (German Sustainable Building Council) assesses the sustainability of various types of buildings. It can be applied to both large-scale private and commercial projects as well as smaller residential buildings. The 2023 version sets high standards for ecological, economic, socio-cultural, and functional aspects throughout the entire life cycle of a building.

Criteria	No. / Relevant building components / construction materials / surfaces	Considered substances / aspects	Quality level
ENV 1.2 Local environmental impact, 03.05.2024 (3rd edition)	2 Coatings on predominantly mineral substrates indoors	VOC / SVOC / preservatives	Quality level 2
Verification: Sicherheitsdatenblatt vom 07.06.2022			

Criteria	No. / Relevant building components / construction materials / surfaces	Considered substances / aspects	Quality level
ENV 1.2 Local environmental impact, 29.05.2025 (4th edition)	2 Coatings on predominantly mineral substrates indoors and on wallpapers, fleeces, plasterboard, etc.	VOC / SVOC / preservatives	Quality level 2
Verification: Sicherheitsdatenblatt vom 07.06.2022			

SENTINEL HOLDING
INSTITUT

Product:
Aton-Sperrgrund

SHI Product Passport no.:
15206-10-1050

KNAUF

DGNB New Construction 2018

The DGNB System (German Sustainable Building Council) assesses the sustainability of various types of buildings. It can be applied to both large-scale private and commercial projects as well as smaller residential buildings.

Criteria	No. / Relevant building components / construction materials / surfaces	Considered substances / aspects	Quality level
ENV 1.2 Local environmental impact	2 Coatings on predominant-ly mineral interior subsur-faces as well as on wallpaper	VOC / SVOC	Quality level 4
Verification: Technisches Datenblatt 10/2021			

SENTINEL HOLDING
INSTITUT

Product:
Aton-Sperrgrund

SHI Product Passport no.:
15206-10-1050

KNAUF

BNB-BN Neubau V2015

The Bewertungssystem Nachhaltiges Bauen (Assessment System for Sustainable Building) is a tool for evaluating public office and administrative buildings, educational facilities, laboratory buildings, and outdoor areas in Germany. The BNB was developed by the former Federal Ministry for the Environment, Nature Conservation, Building and Nuclear Safety (BMUB) and is now overseen by the Federal Ministry for Housing, Urban Development and Building (BMWSB).

Criteria	Pos. / product type	Considered substance group	Quality level
1.1.6 Risiken für die lokale Umwelt	4 Fillers (including quality fillers), dust-binding coatings/primers (according to Decopaint Directive, Category G + H), concrete protective coatings	VOC / hazardous substances	Quality level 5
Verification: Technisches Datenblatt 10/2021			

SENTINEL HOLDING
INSTITUT

Product:
Aton-Sperrgrund

SHI Product Passport no.:
15206-10-1050

KNAUF

EU taxonomy

The EU Taxonomy classifies economic activities and products according to their environmental impact. At the product level, the EU regulation defines clear requirements for harmful substances, formaldehyde and volatile organic compounds (VOCs). The Sentinel Holding Institut GmbH labels qualified products that meet this standard.

Criteria	Product type	Considered substances	Assessment
DNSH - Pollution prevention and control	Sonstige	Stoffe nach Anlage C	compliant
Verification: Sicherheitsdatenblatt vom 07.06.2022			

SENTINEL HOLDING
INSTITUT

Product:
Aton-Sperrgrund

SHI Product Passport no.:
15206-10-1050

KNAUF

BREEAM DE Neubau 2018

BREEAM (Building Research Establishment Environmental Assessment Methodology) is a UK-based building assessment system that evaluates the sustainability of new constructions, refurbishments, and conversions. Developed by the Building Research Establishment (BRE), the system aims to assess and improve the environmental, economic, and social performance of buildings.

Criteria	Product category	Considered substances	Quality level
Hea 02 Indoor Air Quality	Interior paints and coatings	Emissions: Formaldehyde, TVOC, TSVOC, carcinogens	Exemplary quality
Verification: Sicherheitsdatenblatt vom 07.06.2022			

SENTINEL HOLDING
INSTITUT

Product:
Aton-Sperrgrund

SHI Product Passport no.:
15206-10-1050

KNAUF

LEED v4.1

LEED (Leadership in Energy and Environmental Design) is an internationally recognised building certification system developed by the U.S. Green Building Council. It is one of the most widely used sustainability standards for buildings worldwide and is particularly applied in internationally oriented projects. LEED assesses buildings holistically across categories such as energy efficiency, resource conservation, material selection, indoor environmental quality and site sustainability. Depending on the number of points achieved, projects are awarded one of the certification levels: LEED Certified, Silver, Gold or Platinum.

Criteria	Product category	Considered substances	Assessment
EQ Credit: Low-Emitting Materials	Farben und Lacke	Emissionen: Formaldehyd, VOC, Krebserregende Stoffe, VOC-Gehalt	compliant
Verification: Sicherheitsdatenblatt vom 07.06.2022			

SENTINEL HOLDING
INSTITUT

Product:
Aton-Sperrgrund

SHI Product Passport no.:
15206-10-1050

KNAUF

Product labels

In the construction industry, high-quality materials are crucial for a building's indoor air quality and sustainability. Product labels and certificates offer guidance to meet these requirements. However, the evaluation criteria of these labels vary, and it is important to carefully assess them to ensure products align with the specific needs of a construction project.

The EMICODE® label, awarded by the German manufacturers' association "GEV – Gemeinschaft Emissionskontrollierte Verlegewerkstoffe, Klebstoffe und Bauprodukte e. V.", is primarily relevant for flooring installation materials. The EMICODE® EC1^{PLUS} label, as the premium class, sets significantly stricter emission limits than the other label variants.

The IBU ("Institut Bauen und Umwelt e.V.") is an initiative of building product manufacturers committed to sustainability in construction. It serves as the programme operator for Environmental Product Declarations (EPDs) in accordance with the EN 15804 standard. The IBU EPD programme provides comprehensive life cycle assessments and environmental impact data for construction products, supported by independent third-party verification.

Products bearing the Sentinel Holding Institute QNG-ready seal are suitable for projects aiming to achieve the "Qualitätssiegel Nachhaltiges Gebäude" (Quality Seal for Sustainable Buildings). QNG-ready products meet the requirements of QNG Appendix Document 3.1.3, "Avoidance of Harmful Substances in Building Materials." The KfW loan program Climate-Friendly New Construction with QNG may allow for additional funding.

This product is SHI Indoor Air Quality certified and recommended by Sentinel Holding Institut. Indoor-air-focused construction, renovation, and operation of buildings is made possible by transparent and verifiable criteria thanks to the Sentinel Holding concept.

Product:
Aton-Sperrgrund

SHI Product Passport no.:
15206-10-1050

KNAUF

Legal notices

(*) These criteria apply to the construction project as a whole. While individual products can positively contribute to the overall building score through proper planning, the evaluation is always conducted at the building level. The information was provided entirely by the manufacturer.

Find our criteria here: https://www.sentinel-holding.eu/de/Themenwelten/Pr%C3%BCfkriterien%20f%C3%BCr%20Produkte

The SHI Database is the first and only database for construction products whose comprehensive processes and data accuracy are regularly verified by the independent auditing company SGS-TÜV Saar

SGS

SGS TÜV SAAR

Publisher

Sentinel Holding Institut GmbH
Bötzinger Str. 38
79111 Freiburg im Breisgau
Germany
Tel.: +49 761 590 481-70
info@sentinel-holding.eu
www.sentinel-holding.eu



Putz- und Fassadensysteme

K453a.de

Technisches Blatt 10/2021

Aton Sperrgrund

Isolier- und Absperrgrundierung für Putze und Spachtelmassen

Produktbeschreibung

Aton Sperrgrund ist eine gebrauchsfertige Isolier- und Absperr grundierung für Putze, Dünnputze, Spachtelmassen und Oberputze, auf Basis einer Kunstharzdispersion mit feinem Quarzsand gefüllt, weiß pigmentiert und alkalibeständig.

Lagerung

Kühl und frostfrei (+5 °C bis +25 °C) im ungeöffneten Originalgebinde 18 Monate lagerfähig. Anbruchgebinde dicht verschließen. Vor direkter Sonneneinstrahlung oder Wärmeeinwirkung schützen.

Qualität

Das Produkt unterliegt der ständigen werkseigenen Produktionskontrolle.

Eigenschaften und Mehrwert

- Für innen und außen
- Gebrauchsfertig
- Absperrend gegen Lignin und Gilbstoffe
- Schafft griffige Untergründe
- Weiß pigmentiert
- Besonders emissionsarm EC1PLUS
- Verarbeitung von Hand oder maschinell

GEV-EMICODE EC 1 PLUS sehr emissionsarm

www.emicode.com

Anwendungsbereich

Anwendung im Innen- und Außenbereich auf

- Gips-/Gipsfaserplatten und Holzfaser-Dämmplatten, bei denen mit einer Verfärbung durch lösliche Bestandteile oder Durchschlagen von Gilbstoffen gerechnet werden muss
- Fest haftenden Dispersionsanstrichen
- Mineralischen Untergründen

Als absperrende Grundierung vor dem Aufbringen von

- Gipsputzen (z. B. MP 75 L Raumklima, MP 75 Diamant, MP 75 L, MP 75 G/F-Leicht)
- Dünnputzen und Spachtelmassen (z. B. Multi-Finish)
- Mineralischen, dünnlagigen Oberputzen (z. B. Noblo, SP 260 Pro und RP 240 sowie Pico der Feine)
- Pastösen Oberputzen im Außenbereich (z. B. Conni, Addi, Kati)
- Armiermörtel auf Holzfaser-Dämmplatten

Ausführung

Untergrund und Vorbehandlung

Untergrund	Vorbehandlung
Renovierungen und entfernte Tapeten	Kleisterrückstände vollständig entfernen, ggf. schleifen, Schleifstaub entfernen
Leimfarben, abblätternde Farben und sonstige lockere, absandende und mürbe Schichten	Entfernen. Ausbessern, soweit erforderlich
Andere Anstriche	Verträglichkeit ggf. durch Probeanstrich prüfen
Gipsplatten	Entstauben und geschliffene Fugen ggf. mit Tiefengrund oder Grundol vorbehandeln

Vorarbeiten

Der Untergrund muss tragfähig, trocken, fest und ausreichend formstabil sein. Des Weiteren muss der Untergrund staubfrei, frei von losen Teilen, Öl, Fett, Schalungstrenn- und Nachbehandlungsmitteln, Sinterschichten, Verunreinigungen und schädlichen Ausblühungen sein und den Anforderungen an die Ebenheit von Bauteiloberflächen gemäß DIN 18202 entsprechen. Bei kritischem Untergrund sind Vorversuche erforderlich, ggf. Gitterschnitt oder Kratzproben durchführen.

Schmutzempfindliche Bauteile, besonders Glasflächen, Holz, Metalle, Natursteine und Bodenbeläge abdecken bzw. wasserfest abkleben.
Merkblatt „Abklebe- und Abdeckarbeiten für Maler- und Stuckateurarbeiten“ des Bundesverbandes Ausbau und Fassade beachten.

Maschinen/Ausstattung

Maschinelle Verarbeitung mittels Schneckenpumpe (z. B. PFT SWING)

Verarbeitung

Eimerinhalt vor Arbeitsbeginn gut aufrühren. Aton Sperrgrund wird unverdünnt und volldeckend im Kreuzgang mit der Lammfellrolle/Bürste gleichmäßig aufgetragen oder maschinell mit einer geeigneten PFT Förderpumpe, z. B. SWING aufgespritzt und mit der Lammfellrolle eingewalzt. Streifenbildung vermeiden. Bei Verfärbungen durch Lignin, Phenolharz oder ähnlichen Substanzen wird ein zweimaliger Anstrich notwendig. Zwischen den Arbeitsgängen mindestens 12 Stunden Trocknungszeit einhalten. Verunreinigungen durch Knauf Aton Sperrgrund (Spritzer oder Ähnliches) möglichst im noch frischen Zustand mit warmem Wasser von den verunreinigten Flächen wischen. Angetrocknetes Material kann nach Aufweichen mittels nassem Wischtuch o. Ä. entfernt werden.

Trocknung

Mit den Folgearbeiten solange warten, bis Aton Sperrgrund nicht mehr klebt und durchgetrocknet ist (mindestens 12 Stunden bei +20 °C und 65 % rel. Luftfeuchte). Bei kühlen und feuchten Baustellenbedingungen ergeben sich entsprechend längere Trocknungszeiten.
Saugende Untergründe sowie gute Lüftung verkürzen die Trocknungszeiten. Die Zeitspanne nach der Trocknung von Aton Sperrgrund und dem Beginn der Folgearbeiten soll wegen möglicher Baustaubablagerungen gering gehalten werden.

Verarbeitungstemperatur/-klima

Material-, Untergrund- und Lufttemperatur dürfen bei Verarbeitung und bis zur vollständigen Trocknung der Grundierung +5 °C nicht unterschreiten.

Reinigung

Arbeitsgeräte unmittelbar nach Gebrauch mit Wasser reinigen.

Hinweise	Beschichtungen wie dicklagige (Ober-)Putze, Faser-/Wollputze etc., bei denen die Feuchtigkeit lange erhalten bleibt, können trotz Aton Sperrgrund ein Durchschlagen von Lignin aus Gipsplatten verursachen, ggf. ist ein lösemittelhaltiger Voranstrich zu verwenden. Nikotinverunreinigungen können mit Aton Sperrgrund nicht abgesperrt werden.
Achtung	Aton Sperrgrund darf nicht mit anderen Materialien vermischt werden, weil sich dadurch seine Eigenschaften stark ändern können. Bei Holzfaser-Dämmplatten Aton Sperrgrund zweimal auftragen, wobei der zweite Auftrag nicht zu dick erfolgen darf. Eine Gesamtauftragsmenge > 450 g/m^2 muss vermieden werden.

Technische Daten

Bezeichnung	Norm	Einheit	Aton Sperrgrund
Dichte	–	kg/l	ca. 1,3
Viskosität	–	–	Zähflüssig
pH-Wert	–	–	ca. 8
Wasserdampfdiffusionswiderstandszahl μ	–	–	80 – 120

Die technischen Daten wurden nach den jeweils gültigen Prüfnormen ermittelt. Abweichungen davon sind unter Baustellenbedingungen möglich.

Materialbedarf und Verbrauch

Untergrund	Verbrauch je Auftrag g/m²	Ergiebigkeit m²/Eimer
Gips-/Gipsfaserplatten, Holzfaser-Dämmplatten, Dispersionsanstriche, mineralische Untergründe	200 – 250	20 – 25 m² bei 5 kg 80 – 100 m² bei 20 kg

Alle Angaben sind Zirka-Werte und können je nach Untergrund abweichen. Der exakte Materialbedarf ist durch einen Probeauftrag am Objekt zu ermitteln.

Lieferprogramm

Bezeichnung	Ausführung	Verpackungseinheit	Artikelnummer	EAN
Aton Sperrgrund	5 kg	68 Eimer/Palette	00015177	4003950000775
	20 kg	24 Eimer/Palette	00053888	4003950029028

Nachhaltigkeit und Umwelt

Kurzbeschreibung	Einheit	Wert
Vorhandene Zertifikate	–	EC1^{PLUS} (gemäß GEV)
VOC-Gehalt nach RL2004/42/EG	%	≤ 0,1
VOC-Gehalt nach RL2004/42/EG	g/l	≤ 1
Lösemittel- und weichmacherfrei nach VdL-RL01 (Revision 4)	–	Erfüllt

K453a.de Aton Sperrgrund

Isolier- und Absperrgrundierung für Putze und Spachtelmassen

Sicherheitsdatenblatt beachten!
Sicherheitsdatenblätter siehe
pd.knauf.de

Videos für Knauf Systeme und Produkte sind unter folgendem Link zu finden:
youtube.com/knauf

Ausschreibungstexte für alle Knauf Systeme und Produkte mit Exportfunktionen für Word, PDF und GAEB
ausschreibungscenter.de

Mit der Tablet App Knauf Infothek stehen jetzt alle Informationen und Dokumente der Knauf Gips KG jederzeit und an jedem Ort immer aktuell, übersichtlich und bequem zur Verfügung.
knauf.de/infothek

Knauf Direkt
Technischer Auskunft-Service:
Tel.: 09001 31-2000 *
knauf-direkt@knauf.com

www.knauf.de

Knauf Gips KG Am Bahnhof 7, 97346 Iphofen

* Ein Anruf bei Knauf Direkt wird mit 0,39 €/Min. berechnet. Anrufer, die nicht mit Telefonnummer in der Knauf Gips KG Adressdatenbank hinterlegt sind, z. B. private Bauherren oder Nicht-Kunden, zahlen 1,69 €/Min. aus dem deutschen Festnetz. Mobilfunk-Anrufe können abweichen, sie sind abhängig vom Netzbetreiber und Tarif.

Technische Änderungen vorbehalten. Es gilt die jeweils aktuelle Auflage. Die enthaltenen Angaben entsprechen unserem derzeitigen Stand der Technik. Die allgemein anerkannten Regeln der Bautechnik, einschlägige Normen, Richtlinien und handwerklichen Regeln müssen vom Ausführenden neben den Verarbeitungsvorschriften beachtet werden. Unsere Gewährleistung bezieht sich nur auf die einwandfreie Beschaffenheit unseres Materials. Verbrauchs-, Mengen- und Ausführungsangaben sind Erfahrungswerte, die im Falle abweichender Gegebenheiten nicht ohne weiteres übertragen werden können. Alle Rechte vorbehalten. Änderungen, Nachdruck und fotomechanische sowie elektronische Wiedergabe, auch auszugsweise, bedürfen unserer ausdrücklichen Genehmigung.

K453a.de/ger/10.21/0/TB

Konstruktive, statische und bauphysikalische Eigenschaften von Knauf Systemen können nur gewährleistet werden, wenn ausschließlich Knauf Systemkomponenten oder von Knauf empfohlene Produkte verwendet werden.

Aton Sperrgrund

Sicherheitsdatenblatt

gemäß REACH-Verordnung (EG) 1907/2006 einschließlich Änderungsverordnung (EU) 2020/878
Ausgabedatum: 13.05.2026 Überarbeitungsdatum: 13.05.2026 Ersetzt Version vom: 27.01.2026 Version: 8.3

ABSCHNITT 1: Bezeichnung des Stoffs beziehungsweise des Gemischs und des Unternehmens

1.1. Produktidentifikator

Produktform	:	Gemisch
Produktname	:	Aton Sperrgrund
Produkt-Code	:	10254_0010

1.2. Relevante identifizierte Verwendungen des Stoffs oder Gemischs und Verwendungen, von denen abgeraten wird

1.2.1. Relevante identifizierte Verwendungen

Für die Allgemeinheit bestimmt

Hauptverwendungskategorie	:	Verwendung durch Verbraucher,Gewerbliche Nutzung
Verwendung des Stoffs/des Gemischs	:	Grundierungen

1.2.2. Verwendungen, von denen abgeraten wird

Einschränkungen der Anwendung	:	Nur für solche Zwecke verwenden, für die das Produkt bestimmt ist

1.3. Einzelheiten zum Lieferanten, der das Sicherheitsdatenblatt bereitstellt

Hersteller
Knauf Gips KG
Am Bahnhof 7
DE 97346 Iphofen, Bayern
Deutschland
T +49 9323/31-0, F +49 9323/31-277
sds-info@knauf.com, www.knauf.com

Technische Auskunft
Technischer Auskunft-Service Putz und Fassade
T +49 (0) 9323/916-3222 nur für gewerbliche Anwender (Information zur Registrierung, s. Abschnitt 16)
knauf-direkt@knauf.com

1.4. Notrufnummer

Land/Region	Organisation/Firma	Anschrift	Notrufnummer	Anmerkung
Europa	Global Incident Response (GIR) Hotline		+1 760 476 3962	Access Code: 336325

ABSCHNITT 2: Mögliche Gefahren

2.1. Einstufung des Stoffs oder Gemischs

Einstufung gemäß Verordnung (EG) Nr. 1272/2008 [CLP]

Nicht eingestuft

Schädliche physikalisch-chemische, gesundheitliche und Umwelt-Wirkungen

Keine weiteren Informationen verfügbar

2.2. Kennzeichnungselemente

Kennzeichnung gemäß Verordnung (EG) Nr. 1272/2008 [CLP]

Sicherheitshinweise (CLP)	:	P102 - Darf nicht in die Hände von Kindern gelangen. P262 - Nicht in die Augen, auf die Haut oder auf die Kleidung gelangen lassen.
EUH Sätze	:	EUH210 - Sicherheitsdatenblatt auf Anfrage erhältlich. EUH208 - Enthält Reaktionsmasse aus 5-Chlor-2-methyl-2H-isothiazol-3-on und 2-Methyl-2H-isothiazol-3-on (3:1), 1,2-Benzisothiazol-3(2H)-on; 1,2-Benzisothiazolin-3-on. Kann allergische Reaktionen hervorrufen.
Zusätzliche Sätze	:	Behandelte Ware gemäß Verordnung (EU) Nr. 528/2012 zur Gewährleistung der Haltbarkeit. Enthält: Biozidprodukte. Biozid-Wirkstoffe: Pyridin-2-thiol-1-oxid, Natriumsalz (3811-73-2), 1,2-Benzisothiazol-3(2H)-on (2634-33-5). GRENZWERTE FÜR DEN VOC-HÖCHSTGEHALT VON FARBEN UND LACKEN.

		Produktunterkategorie: g (Typ: Wb): 30 g/l. VOC-Gehalt: <= 0,1 % (≤ 1 g/L).
Kindergesicherter Verschluss	:	Nicht anwendbar
Tastbarer Gefahrenhinweis	:	Nicht anwendbar

2.3. Sonstige Gefahren

Enthält keine PBT und/oder vPvB-Stoffe ≥ 0,1%, bewertet gemäß REACH Anhang XIII

Komponente	
Stoffe, die die PBT-Kriterien gemäß REACH Anhang XIII nicht erfüllen	Reaktionsmasse aus 5-Chlor-2-methyl-2H-isothiazol-3-on und 2-Methyl-2H-isothiazol-3-on (3:1) (55965-84-9)(¹), Quarz, Konz alveolengängiges kristallines Siliziumdioxid < 1 % (14808-60-7), 1,2-Benzisothiazol-3(2H)-on; 1,2-Benzisothiazolin-3-on (2634-33-5)(¹)
Stoffe, die die vPvB-Kriterien gemäß REACH Anhang XIII nicht erfüllen	Reaktionsmasse aus 5-Chlor-2-methyl-2H-isothiazol-3-on und 2-Methyl-2H-isothiazol-3-on (3:1) (55965-84-9)(¹), Quarz, Konz alveolengängiges kristallines Siliziumdioxid < 1 % (14808-60-7), 1,2-Benzisothiazol-3(2H)-on; 1,2-Benzisothiazolin-3-on (2634-33-5)(¹)

(¹) Stoffe in Konzentrationen unter 0,1 % und die auf freiwilliger Basis genannt werden

Das Gemisch enthält keine Stoffe mit endokrinschädlichen Eigenschaften (gemäß REACH Artikel 59 Absatz 1 oder Verordnung 2017/2100 oder Verordnung 2018/605) in einer Konzentration von ≥ 0,1 %

ABSCHNITT 3: Zusammensetzung/Angaben zu Bestandteilen

3.2. Gemische

Name	Produktidentifikator	%	Einstufung gemäß Verordnung (EG) Nr. 1272/2008 [CLP]
Quarz, Konz alveolengängiges kristallines Siliziumdioxid < 1 % Stoff, für den ein gemeinschaftlicher Grenzwert für die Exposition am Arbeitsplatz gilt	CAS-Nr.: 14808-60-7 EG-Nr.: 238-878-4	< 20	Nicht eingestuft
1,2-Benzisothiazol-3(2H)-on; 1,2-Benzisothiazolin-3-on (Wirkstoff (Biozid))	CAS-Nr.: 2634-33-5 EG-Nr.: 220-120-9 EG Index-Nr.: 613-088-00-6 REACH-Nr.: 01-2120761540-60	< 0,036	Acute Tox. 2 (Inhalativ: Staub, Nebel), H330 (ATE=0,21 mg/l) Acute Tox. 4 (Oral), H302 (ATE=450 mg/kg Körpergewicht) Skin Irrit. 2, H315 Eye Dam. 1, H318 Skin Sens. 1A, H317 Aquatic Acute 1, H400 Aquatic Chronic 1, H410
Reaktionsmasse aus 5-Chlor-2-methyl-2H-isothiazol-3-on und 2-Methyl-2H-isothiazol-3-on (3:1) (Wirkstoff (Biozid))	CAS-Nr.: 55965-84-9 EG Index-Nr.: 613-167-00-5	< 0,0015	Acute Tox. 2 (Inhalativ), H330 Acute Tox. 2 (Dermal), H310 Acute Tox. 3 (Oral), H301 Skin Corr. 1C, H314 Eye Dam. 1, H318 Skin Sens. 1A, H317 Aquatic Acute 1, H400 (M=100) Aquatic Chronic 1, H410 (M=100) EUH071

Spezifische Konzentrationsgrenzwerte:

Name	Produktidentifikator	Spezifische Konzentrationsgrenzwerte (%)
1,2-Benzisothiazol-3(2H)-on; 1,2-Benzisothiazolin-3-on (Wirkstoff (Biozid))	CAS-Nr.: 2634-33-5 EG-Nr.: 220-120-9 EG Index-Nr.: 613-088-00-6 REACH-Nr.: 01-2120761540-60	(0,036 ≤ C ≤ 100) Skin Sens. 1A; H317
Reaktionsmasse aus 5-Chlor-2-methyl-2H-isothiazol-3-on und 2-Methyl-2H-isothiazol-3-on (3:1) (Wirkstoff (Biozid))	CAS-Nr.: 55965-84-9 EG Index-Nr.: 613-167-00-5	(0,0015 ≤ C ≤ 100) Skin Sens. 1A; H317 (0,06 ≤ C < 0,6) Skin Irrit. 2; H315 (0,06 ≤ C < 0,6) Eye Irrit. 2; H319 (0,6 ≤ C ≤ 100) Eye Dam. 1; H318 (0,6 ≤ C ≤ 100) Skin Corr. 1C; H314

Wortlaut der H- und EUH-Sätze: siehe Abschnitt 16

ABSCHNITT 4: Erste-Hilfe-Maßnahmen

4.1. Beschreibung der Erste-Hilfe-Maßnahmen

Erste-Hilfe-Maßnahmen allgemein : Verunreinigten Kleidungsstücke und Schuhe ausziehen.

Erste-Hilfe-Maßnahmen nach Einatmen : Die Person an die frische Luft bringen und für ungehinderte Atmung sorgen. Bei Unwohlsein ärztlichen Rat einholen/ärztliche Hilfe hinzuziehen.

Erste-Hilfe-Maßnahmen nach Hautkontakt : Haut abspülen und dann gründlich mit Wasser und Seife waschen. Keine Lösemittel oder Verdünnungen verwenden.

Erste-Hilfe-Maßnahmen nach Augenkontakt : Sofort mit viel Wasser ausspülen. Eventuell vorhandene Kontaktlinsen nach Möglichkeit entfernen. Weiter ausspülen. Bei anhaltender Augenreizung: Ärztlichen Rat einholen/ärztliche Hilfe hinzuziehen.

Erste-Hilfe-Maßnahmen nach Verschlucken : Mund gründlich mit Wasser ausspülen. Reichlich Wasser trinken. Ärztlichen Rat einholen/ärztliche Hilfe hinzuziehen.

4.2. Wichtigste akute und verzögert auftretende Symptome und Wirkungen

Keine weiteren Informationen verfügbar

4.3. Hinweise auf ärztliche Soforthilfe oder Spezialbehandlung

Keine weiteren Informationen verfügbar

ABSCHNITT 5: Maßnahmen zur Brandbekämpfung

5.1. Löschmittel

Geeignete Löschmittel : Material ist nicht entzündbar. Bei Umgebungsbrand Löschmittel anpassen an Umgebung. Wassersprühstrahl. Schaum. Trockenlöschpulver. Kohlendioxid.

Ungeeignete Löschmittel : Wasser im Vollstrahl.

5.2. Besondere vom Stoff oder Gemisch ausgehende Gefahren

Keine weiteren Informationen verfügbar

5.3. Hinweise für die Brandbekämpfung

Schutz bei der Brandbekämpfung : Umgebungsluft-unabhängiges Atemschutzgerät. Vollständige Schutzkleidung.

ABSCHNITT 6: Maßnahmen bei unbeabsichtigter Freisetzung

6.1. Personenbezogene Vorsichtsmaßnahmen, Schutzausrüstungen und in Notfällen anzuwendende Verfahren

Allgemeine Maßnahmen : Für ausreichende Lüftung sorgen.

6.1.1. Nicht für Notfälle geschultes Personal

Keine weiteren Informationen verfügbar

6.1.2. Einsatzkräfte

Keine weiteren Informationen verfügbar

6.2. Umweltschutzmaßnahmen

Eindringen in Kanalisation und öffentliche Gewässer verhindern. Freisetzung in die Umwelt vermeiden. Falls die Flüssigkeit in die Kanalisation oder öffentliche Gewässer gelangt, sind die Behörden zu benachrichtigen.

6.3. Methoden und Material für Rückhaltung und Reinigung

Zur Rückhaltung : Mit viel flüssigkeitsbindendem Material (z.B. Sand, Kieselgur, Säurebinder, Universalbinder) aufnehmen. Entsorgung muss gemäß den behördlichen Vorschriften erfolgen.

Sonstige Angaben : Bereich mit verschüttetem Material kann rutschig sein.

6.4. Verweis auf andere Abschnitte

7.1. Schutzmaßnahmen zur sicheren Handhabung. 8. Begrenzung und Überwachung der Exposition/Persönliche Schutzausrüstungen. Weitere Angaben siehe Abschnitt 13.

ABSCHNITT 7: Handhabung und Lagerung

7.1. Schutzmaßnahmen zur sicheren Handhabung

Schutzmaßnahmen zur sicheren Handhabung : Berührung mit den Augen und der Haut vermeiden. Gas / Rauch / Dampf / Aerosol nicht einatmen. Beim Versprühen Einatmen des Aerosols vermeiden. Bereich gründlich lüften. Unbefugten Personen den Zutritt verwehren.

Hygienemaßnahmen : Bei Gebrauch nicht essen, trinken oder rauchen. Von Nahrungsmitteln, Getränken und Futtermitteln fernhalten. Kontaminierte Kleidung vor erneutem Tragen waschen. Hände waschen vor den Pausen und nach der Arbeit.

7.2. Bedingungen zur sicheren Lagerung unter Berücksichtigung von Unverträglichkeiten

Lagerbedingungen : Nur im Originalbehälter aufbewahren. Vor Frost schützen. Vor Sonnenbestrahlung schützen. An einem gut belüfteten Ort aufbewahren.

Lagertemperatur : 5 – 25 °C

7.3. Spezifische Endanwendungen

Keine weiteren Informationen verfügbar

ABSCHNITT 8: Begrenzung und Überwachung der Exposition/Persönliche Schutzausrüstungen

8.1. Zu überwachende Parameter

8.1.1 Nationale Grenzwerte für die berufsbedingte Exposition und biologische Grenzwerte

Quarz, Konz alveolengängiges kristallines Siliziumdioxid < 1 % (14808-60-7)	
EU - Richt-Arbeitsplatzgrenzwert (IOEL)	
Lokale Bezeichnung	Silica crystaline (Quartz)
IOEL TWA	0,05 mg/m³ (respirable dust)
Anmerkung	(Year of adoption 2003)
Rechtlicher Bezug	SCOEL Recommendations
EU - Arbeitsplatzgrenzwert (BOEL)	
Lokale Bezeichnung	Respirable crystalline silica dust
BOEL TWA	0,1 mg/m³ (Respirable fraction)
Rechtlicher Bezug	DIRECTIVE (EU) 2019/130 (amending Directive 2004/37/EC)

8.1.2. Empfohlene Überwachungsverfahren

Keine weiteren Informationen verfügbar

8.1.3. Freigesetzte Luftverunreinigungen

Keine weiteren Informationen verfügbar

8.1.4. DNEL- und PNEC-Werte

Keine weiteren Informationen verfügbar

8.1.5. Control banding

Keine weiteren Informationen verfügbar


8.2. Begrenzung und Überwachung der Exposition

8.2.1. Geeignete technische Steuerungseinrichtungen

Keine weiteren Informationen verfügbar

8.2.2. Persönliche Schutzausrüstung

Persönliche Schutzausrüstung:
Bei der Arbeit geeignete Schutzkleidung tragen.
Persönliche Schutzausrüstung - Symbol(e):



8.2.2.1. Augen- und Gesichtsschutz

Augenschutz:
Spritzschutzbrille tragen, wenn Augenkontakt durch Verspritzen möglich ist

Augenschutz			
Typ	**Einsatzbereich**	**Kennzeichnungen**	**Norm**
Schutzbrille mit Seitenschutz			

8.2.2.2. Hautschutz

Handschutz:
Schutzhandschuhe

8.2.2.3. Atemschutz

Atemschutz:
Bei Einwirkungen von Dämpfen, Stäuben und Aerosolen ist Atemschutz zu verwenden. Beim Versprühen geeignete Atemschutzausrüstung tragen

8.2.2.4. Thermische Gefahren

Keine weiteren Informationen verfügbar

8.2.3. Begrenzung und Überwachung der Umweltexposition

Begrenzung und Überwachung der Verbraucherexposition:
Bei Tätigkeiten mit starker Dispersion, die zu einem erheblichen Aerosol-oder Dampf-Ausstoß führen könnten, z.B. durch Sprühen, sind sonstige Schutzmaßnahmen wie die Abtrennung der Tätigkeit, die Personalminimierung, das Tragen von Atemschutzgeräten, flüssigkeitsabweisenden Schutzanzügen und eines Gesichtsschutzes vorzusehen.

ABSCHNITT 9: Physikalische und chemische Eigenschaften

9.1. Angaben zu den grundlegenden physikalischen und chemischen Eigenschaften

Aggregatzustand	:	Flüssig
Farbe	:	Weiß.
Geruch	:	Leicht.
Geruchsschwelle	:	Nicht verfügbar
Schmelzpunkt	:	Nicht verfügbar
Gefrierpunkt	:	Nicht verfügbar
Siedepunkt	:	≈ 100 °C
Entzündbarkeit	:	Nicht verfügbar
Explosive Eigenschaften	:	Das Produkt ist nicht explosionsgefährlich.
Untere Explosionsgrenze	:	Nicht verfügbar

Obere Explosionsgrenze	:	Nicht verfügbar
Flammpunkt	:	Nicht verfügbar
Zündtemperatur	:	Nicht verfügbar
Zersetzungstemperatur	:	Nicht verfügbar
pH-Wert	:	≈ 9 (20 °C)
Viskosität, kinematisch	:	Nicht verfügbar
Löslichkeit	:	vollkommen mischbar.
Verteilungskoeffizient n-Oktanol/Wasser (Log Kow)	:	Nicht verfügbar
Dampfdruck	:	Nicht verfügbar
Dampfdruck bei 50°C	:	Nicht verfügbar
Dichte	:	≈ 1,3 g/cm³
Relative Dichte	:	Nicht verfügbar
Relative Dampfdichte bei 20°C	:	Nicht verfügbar
Partikeleigenschaften	:	Nicht anwendbar

9.2. Sonstige Angaben

9.2.1. Angaben über physikalische Gefahrenklassen

Keine weiteren Informationen verfügbar

9.2.2. Sonstige sicherheitstechnische Kenngrößen

VOC-Gehalt : ≤ 0,1 % (≤ 1 g/L)

ABSCHNITT 10: Stabilität und Reaktivität

10.1. Reaktivität

Das Produkt ist nicht reaktiv unter normalen Gebrauchs-, Lagerungs- und Transportbedingungen.

10.2. Chemische Stabilität

Unter normalen Anwendungsbedingungen stabil.

10.3. Möglichkeit gefährlicher Reaktionen

Keine - bei bestimmungsgemäßer Verwendung.

10.4. Zu vermeidende Bedingungen

Keine unter den empfohlenen Lagerungs- und Handhabungsbedingungen (siehe Abschnitt 7).

10.5. Unverträgliche Materialien

Keine Information verfügbar.

10.6. Gefährliche Zersetzungsprodukte

Unter normalen Lager- und Anwendungsbedingungen sollten keine gefährlichen Zersetzungsprodukte gebildet werden.

ABSCHNITT 11: Toxikologische Angaben

11.1. Angaben zu den Gefahrenklassen im Sinne der Verordnung (EG) Nr. 1272/2008

Akute Toxizität (Oral)	:	Nicht eingestuft (Aufgrund der verfügbaren Daten sind die Einstufungskriterien nicht erfüllt)
Akute Toxizität (Dermal)	:	Nicht eingestuft (Aufgrund der verfügbaren Daten sind die Einstufungskriterien nicht erfüllt)
Akute Toxizität (inhalativ)	:	Nicht eingestuft (Aufgrund der verfügbaren Daten sind die Einstufungskriterien nicht erfüllt)

Reaktionsmasse aus 5-Chlor-2-methyl-2H-isothiazol-3-on und 2-Methyl-2H-isothiazol-3-on (3:1) (55965-84-9)	
LD50 (oral, Ratte)	66 mg/kg Körpergewicht (OECD 401: Akute Orale Toxizität, Ratte, Männlich / weiblich, Experimenteller Wert, Berechnet im Verhältnis zum Wirkstoff, Oral, 14 Tag(e))
LD50 (dermal, Ratte)	> 141 mg/kg Körpergewicht (OECD 402: Akute Dermale Toxizität, 24 Stdn, Ratte, Männlich / weiblich, Experimenteller Wert, Dermal, 14 Tag(e))
LC50 inhalativ - Ratte	0,17 mg/l air (OECD 403, 4 Stdn, Ratte, Männlich / weiblich, Experimenteller Wert, Berechnet im Verhältnis zum Wirkstoff, Inhalation (Stäube), 14 Tag(e))

1,2-Benzisothiazol-3(2H)-on; 1,2-Benzisothiazolin-3-on (2634-33-5)	
LD50 (oral, Ratte)	490 mg/kg Körpergewicht (Äquivalent oder vergleichbar mit OECD 401, Ratte, Männlich / weiblich, Experimenteller Wert, Oral, 14 Tag(e))
LD50 (dermal, Ratte)	> 2000 mg/kg Körpergewicht (OECD 402: Akute Dermale Toxizität, 24 Stdn, Ratte, Männlich / weiblich, Experimenteller Wert, Dermal, 14 Tag(e))

Ätz-/Reizwirkung auf die Haut : Nicht eingestuft (Aufgrund der verfügbaren Daten sind die Einstufungskriterien nicht erfüllt)
pH-Wert: ≈ 9 (20 °C)

Reaktionsmasse aus 5-Chlor-2-methyl-2H-isothiazol-3-on und 2-Methyl-2H-isothiazol-3-on (3:1) (55965-84-9)	
pH-Wert	Keine Daten in der Literatur vorhanden

Quarz, Konz alveolengängiges kristallines Siliziumdioxid < 1 % (14808-60-7)	
pH-Wert	6 – 7

1,2-Benzisothiazol-3(2H)-on; 1,2-Benzisothiazolin-3-on (2634-33-5)	
pH-Wert	Keine Daten in der Literatur vorhanden

Schwere Augenschädigung/-reizung : Nicht eingestuft (Aufgrund der verfügbaren Daten sind die Einstufungskriterien nicht erfüllt)
pH-Wert: ≈ 9 (20 °C)

Reaktionsmasse aus 5-Chlor-2-methyl-2H-isothiazol-3-on und 2-Methyl-2H-isothiazol-3-on (3:1) (55965-84-9)	
pH-Wert	Keine Daten in der Literatur vorhanden

Quarz, Konz alveolengängiges kristallines Siliziumdioxid < 1 % (14808-60-7)	
pH-Wert	6 – 7

1,2-Benzisothiazol-3(2H)-on; 1,2-Benzisothiazolin-3-on (2634-33-5)	
pH-Wert	Keine Daten in der Literatur vorhanden

Sensibilisierung der Atemwege/Haut : Nicht eingestuft (Aufgrund der verfügbaren Daten sind die Einstufungskriterien nicht erfüllt)

Keimzellmutagenität : Nicht eingestuft (Aufgrund der verfügbaren Daten sind die Einstufungskriterien nicht erfüllt)

Karzinogenität : Nicht eingestuft (Aufgrund der verfügbaren Daten sind die Einstufungskriterien nicht erfüllt)

Quarz, Konz alveolengängiges kristallines Siliziumdioxid < 1 % (14808-60-7)	
IARC-Gruppe	1 - Kanzerogen für den Menschen

Reproduktionstoxizität : Nicht eingestuft (Aufgrund der verfügbaren Daten sind die Einstufungskriterien nicht erfüllt)

Spezifische Zielorgan-Toxizität bei einmaliger Exposition : Nicht eingestuft (Aufgrund der verfügbaren Daten sind die Einstufungskriterien nicht erfüllt)

Spezifische Zielorgan-Toxizität bei wiederholter Exposition : Nicht eingestuft (Aufgrund der verfügbaren Daten sind die Einstufungskriterien nicht erfüllt)

Aspirationsgefahr : Nicht eingestuft (Aufgrund der verfügbaren Daten sind die Einstufungskriterien nicht erfüllt)

Reaktionsmasse aus 5-Chlor-2-methyl-2H-isothiazol-3-on und 2-Methyl-2H-isothiazol-3-on (3:1) (55965-84-9)	
Viskosität, kinematisch	Nicht anwendbar (Feststoff)

Quarz, Konz alveolengängiges kristallines Siliziumdioxid < 1 % (14808-60-7)	
Viskosität, kinematisch	Nicht anwendbar (Feststoff)

1,2-Benzisothiazol-3(2H)-on; 1,2-Benzisothiazolin-3-on (2634-33-5)	
Viskosität, kinematisch	Nicht anwendbar (Feststoff)

11.2. Angaben über sonstige Gefahren

11.2.1. Endokrinschädliche Eigenschaften

Gesundheitlichen Auswirkungen, die durch diese endokrinschädlichen Eigenschaften verursacht werden können : Das Gemisch enthält keine Stoffe mit endokrinschädlichen Eigenschaften (gemäß REACH Artikel 59 Absatz 1 oder Verordnung 2017/2100 oder Verordnung 2018/605) in einer Konzentration von ≥ 0,1 %

11.2.2. Sonstige Angaben

Keine weiteren Informationen verfügbar

ABSCHNITT 12: Umweltbezogene Angaben

12.1. Toxizität

Gewässergefährdend, kurzfristige (akut) : Nicht eingestuft (Aufgrund der verfügbaren Daten sind die Einstufungskriterien nicht erfüllt)

Gewässergefährdend, langfristige (chronisch) : Nicht eingestuft (Aufgrund der verfügbaren Daten sind die Einstufungskriterien nicht erfüllt)

Reaktionsmasse aus 5-Chlor-2-methyl-2H-isothiazol-3-on und 2-Methyl-2H-isothiazol-3-on (3:1) (55965-84-9)	
LC50 - Fisch [1]	0,19 mg/l (EPA OPP 72-1, 96 Stdn, Oncorhynchus mykiss, Durchflusssystem, Süßwasser, Experimenteller Wert, GLP)
EC50 - Krebstiere [1]	0,007 mg/l (48 Stdn, Acartia tonsa, Salzwasser, Experimenteller Wert, GLP)
ErC50 Algen	19,9 µg/l (OECD 201: Algen, Wachstumshemmungstest, 72 Stdn, Skeletonema costatum, Statisches System, Salzwasser, Experimenteller Wert, GLP)

1,2-Benzisothiazol-3(2H)-on; 1,2-Benzisothiazolin-3-on (2634-33-5)	
LC50 - Fisch [1]	2,2 mg/l (OECD 203: Fisch, Test zur akuten Toxizität, 96 Stdn, Oncorhynchus mykiss, Statisches System, Experimenteller Wert, Nominale Konzentration)
EC50 - Krebstiere [1]	2,9 mg/l (OECD 202: Daphnia sp. Akuter Immobilisationstest, 48 Stdn, Daphnia magna, Statisches System, Experimenteller Wert, Tödlich)
ErC50 Algen	150 µg/l (OECD 201: Algen, Wachstumshemmungstest, 72 Stdn, Pseudokirchneriella subcapitata, Experimenteller Wert, GLP)

12.2. Persistenz und Abbaubarkeit

Aton Sperrgrund	
Persistenz und Abbaubarkeit	Schnell abbaubar

Reaktionsmasse aus 5-Chlor-2-methyl-2H-isothiazol-3-on und 2-Methyl-2H-isothiazol-3-on (3:1) (55965-84-9)	
Persistenz und Abbaubarkeit	Nicht leicht biologisch abbaubar im Wasser.

Quarz, Konz alveolengängiges kristallines Siliziumdioxid < 1 % (14808-60-7)	
Persistenz und Abbaubarkeit	Biologische Abbaubarkeit: nicht anwendbar, Keine (experimentellen) Daten zur Mobilität des Stoffes vorhanden.
Chemischer Sauerstoffbedarf (CSB)	Nicht anwendbar
ThSB	Nicht anwendbar

1,2-Benzisothiazol-3(2H)-on; 1,2-Benzisothiazolin-3-on (2634-33-5)	
Persistenz und Abbaubarkeit	Nicht leicht biologisch abbaubar im Wasser.

12.3. Bioakkumulationspotenzial

Reaktionsmasse aus 5-Chlor-2-methyl-2H-isothiazol-3-on und 2-Methyl-2H-isothiazol-3-on (3:1) (55965-84-9)	
BKF - Fisch [1]	41 – 54 (OECD 305, 28 Tag(e), Lepomis macrochirus, Durchflusssystem, Süßwasser, Experimenteller Wert, Frischgewicht)

Reaktionsmasse aus 5-Chlor-2-methyl-2H-isothiazol-3-on und 2-Methyl-2H-isothiazol-3-on (3:1) (55965-84-9)	
Verteilungskoeffizient n-Oktanol/Wasser (Log Pow)	-0,32 – 0,7 (Experimenteller Wert, OECD 117: Verteilungskoeffizient (n-Oktanol/Wasser), HPLC-Methode, 20 °C)
Bioakkumulationspotenzial	Niedriges Potenzial für Bioakkumulation (BCF < 500).

Quarz, Konz alveolengängiges kristallines Siliziumdioxid < 1 % (14808-60-7)	
Bioakkumulationspotenzial	Angaben zur Bioakkumulation nicht vorhanden.

1,2-Benzisothiazol-3(2H)-on; 1,2-Benzisothiazolin-3-on (2634-33-5)	
BKF - Fisch [1]	6,6 (Äquivalent oder vergleichbar mit OECD 305, 56 Tag(e), Lepomis macrochirus, Experimenteller Wert, Frischgewicht)
Verteilungskoeffizient n-Oktanol/Wasser (Log Pow)	-0,9 – 0,99 (Experimenteller Wert, EU Methode A.8, 20 °C)
Bioakkumulationspotenzial	Niedriges Potenzial für Bioakkumulation (BCF < 500).

12.4. Mobilität im Boden

Reaktionsmasse aus 5-Chlor-2-methyl-2H-isothiazol-3-on und 2-Methyl-2H-isothiazol-3-on (3:1) (55965-84-9)	
Oberflächenspannung	Keine Daten in der Literatur vorhanden
Normalisierter Adsorptionskoeffizient für organischen Kohlenstoff (Log Koc)	0,81 – 1 (log Koc, Berechnungswert)
Ökologie - Boden	Sehr mobil im Boden.

Quarz, Konz alveolengängiges kristallines Siliziumdioxid < 1 % (14808-60-7)	
Oberflächenspannung	Keine Daten in der Literatur vorhanden
Ökologie - Boden	Geringes Potenzial für Mobilität im Boden.

1,2-Benzisothiazol-3(2H)-on; 1,2-Benzisothiazolin-3-on (2634-33-5)	
Oberflächenspannung	72,6 mN/m (20 °C, 0.1 %, EU Methode A.5)
Normalisierter Adsorptionskoeffizient für organischen Kohlenstoff (Log Koc)	0,97 (log Koc, OECD 121: Schätzung des Adsorptionskoeffizienten (Koc) im Boden und in Klärschlamm mittels Hochdruck-Flüssigchromatographie (HPLC), Experimenteller Wert, GLP)
Ökologie - Boden	Sehr mobil im Boden.

12.5. Ergebnisse der PBT- und vPvB-Beurteilung

Komponente	
Stoffe, die die PBT-Kriterien gemäß REACH Anhang XIII nicht erfüllen	Reaktionsmasse aus 5-Chlor-2-methyl-2H-isothiazol-3-on und 2-Methyl-2H-isothiazol-3-on (3:1) (55965-84-9)(¹), Quarz, Konz alveolengängiges kristallines Siliziumdioxid < 1 % (14808-60-7), 1,2-Benzisothiazol-3(2H)-on; 1,2-Benzisothiazolin-3-on (2634-33-5)(¹)
Stoffe, die die vPvB-Kriterien gemäß REACH Anhang XIII nicht erfüllen	Reaktionsmasse aus 5-Chlor-2-methyl-2H-isothiazol-3-on und 2-Methyl-2H-isothiazol-3-on (3:1) (55965-84-9)(¹), Quarz, Konz alveolengängiges kristallines Siliziumdioxid < 1 % (14808-60-7), 1,2-Benzisothiazol-3(2H)-on; 1,2-Benzisothiazolin-3-on (2634-33-5)(¹)

(¹) Stoffe in Konzentrationen unter 0,1 % und die auf freiwilliger Basis genannt werden

12.6. Endokrinschädliche Eigenschaften

Schädliche Wirkungen auf die Umwelt aufgrund endokrinschädlicher Eigenschaften : Das Gemisch enthält keine Stoffe mit endokrinschädlichen Eigenschaften (gemäß REACH Artikel 59 Absatz 1 oder Verordnung 2017/2100 oder Verordnung 2018/605) in einer Konzentration von ≥ 0,1 %.

12.7. Andere schädliche Wirkungen

Keine weiteren Informationen verfügbar

ABSCHNITT 13: Hinweise zur Entsorgung

13.1. Verfahren der Abfallbehandlung

Regionale Abfallverordnung	:	Entsorgung muss gemäß den behördlichen Vorschriften erfolgen.
Verfahren der Abfallbehandlung	:	Ausgehärtete Produktrückstände möglichst staubfrei handhaben.
Empfehlungen für die Produkt-/Verpackung-Abfallentsorgung	:	Verpackungen erst nach vorheriger Reinigung entsorgen. Entsorgung muss gemäß den behördlichen Vorschriften erfolgen. Sorgfältig gereinigte Verpackungen einer dafür zugelassenen Sammelstelle übergeben.
Europäisches Abfallverzeichnis (LoW, EG 2000/532)	:	08 01 20 - wässrige Suspensionen, die Farben oder Lacke enthalten, mit Ausnahme derjenigen, die unter 08 01 19 fallen

ABSCHNITT 14: Angaben zum Transport

Gemäß ADR / IMDG / IATA / ADN / RID

ADR	IMDG	IATA	ADN	RID
14.1. UN-Nummer oder ID-Nummer				
Nicht anwendbar	Nicht anwendbar	Nicht anwendbar	Nicht anwendbar	Nicht anwendbar
14.2. Ordnungsgemäße UN-Versandbezeichnung				
Nicht anwendbar	Nicht anwendbar	Nicht anwendbar	Nicht anwendbar	Nicht anwendbar
14.3. Transportgefahrenklassen				
Nicht anwendbar	Nicht anwendbar	Nicht anwendbar	Nicht anwendbar	Nicht anwendbar
14.4. Verpackungsgruppe				
Nicht anwendbar	Nicht anwendbar	Nicht anwendbar	Nicht anwendbar	Nicht anwendbar
14.5. Umweltgefahren				
Nicht anwendbar	Nicht anwendbar	Nicht anwendbar	Nicht anwendbar	Nicht anwendbar
Keine zusätzlichen Informationen verfügbar				

14.6. Besondere Vorsichtsmaßnahmen für den Verwender

Landtransport
Nicht anwendbar

Seeschiffstransport
Nicht anwendbar

Lufttransport
Nicht anwendbar

Binnenschiffstransport
Nicht anwendbar

Bahntransport
Nicht anwendbar

14.7. Massengutbeförderung auf dem Seeweg gemäß IMO-Instrumenten

Nicht anwendbar

ABSCHNITT 15: Rechtsvorschriften

15.1. Vorschriften zu Sicherheit, Gesundheits- und Umweltschutz/spezifische Rechtsvorschriften für den Stoff oder das Gemisch

15.1.1. EU-Verordnungen

Sonstige Vorschriften, Beschränkungen und Verbotsverordnungen : Richtlinie 2004/42/EG zur Begrenzung der Emissionen flüchtiger organischer Verbindungen aufgrund der Verwendung organischer Lösungsmittel in bestimmten Farben und Lacken und Produkten zur Fahrzeugreparaturlackierung. GRENZWERTE FÜR DEN VOC-HÖCHSTGEHALT VON FARBEN UND LACKEN. Produktunterkategorie: h (Typ: Wb): 30 g/L.

REACH Anhang XVII (Beschränkungsliste)

Enthält keine Stoffe, die im REACH-Anhang XVII (Beschränkungsbedingungen) gelistet sind

REACH Anhang XIV (Zulassungsliste)

Enthält keine Stoffe, die in REACH Anhang XIV gelistet sind

REACH Kandidatenliste (SVHC)

Enthält keine Stoffe, die auf der REACH-Kandidatenliste gelistet sind

PIC-Verordnung (Vorherige Zustimmung nach Inkenntnissetzung)

Enthält keine Stoffe, die in der PIC-Verordnung gelistet sind (EU 649/2012, Aus- und Einfuhr gefährlicher Chemikalien)

POP-Verordnung (Persistente Organische Schadstoffe)

Enthält keine Stoffe, die in der POP-Verordnung gelistet sind (EU 2019/1021, Persistente Organische Schadstoffe)

Ozon-Verordnung (2024/590)

Enthält keine Stoffe, die in der Ozon-Abbau-Liste gelistet sind (Verordnung EU 2024/590, Stoffe die zum Abbau der Ozonschicht führen)

Verordnung zu Gütern mit doppeltem Verwendungszweck (Dual-Use-Verordnung)

Enthält keine Stoffe, die in der Dual-Use-Verordnung gelistet sind

VOC-Richtlinie (2004/42)

VOC-Gehalt : ≤ 0,1 % (≤ 1 g/L)

Explosivstoff-Ausgangsstoff-Verordnung (EU 2019/1148)

Enthält keine Stoffe, die in der Explosivstoff-Ausgangsstoff-Verordnung gelistet sind (EU 2019/1148)

Drogen-Ausgangsstoff-Verordnung (EG 273/2004)

Enthält keine Stoffe, die in der Drogen-Ausgangsstoff-Verordnung gelistet sind (EG 273/2004, Stoffe die bei der unerlaubten Herstellung von Suchtstoffen und psychotropen Substanzen verwendet werden)

15.1.2. Nationale Vorschriften

Deutschland

Beschäftigungsbeschränkungen : Beschäftigungsverbote oder -beschränkungen Jugendlicher nach § 22 JArbSchG bei Entstehung von Gefahrstoffen beachten.

GISCODE : BSW20 - Beschichtungsstoffe, wasserbasiert.

Wassergefährdungsklasse (WGK) : WGK 1, Schwach wassergefährdend (Einstufung nach AwSV, Anlage 1).

Lagerklasse (LGK, TRGS 510) : LGK 12 - Nicht brennbare Flüssigkeiten.

VOC-Gehalt : ≤ 0,1 % (≤ 1 g/L)

15.2. Stoffsicherheitsbeurteilung

Stoffsicherheitsbeurteilungen für Stoffe, die in diesem Gemisch enthalten sind, wurden nicht durchgeführt

ABSCHNITT 16: Sonstige Angaben

Änderungshinweise

Abschnitt	Geändertes Element	Anmerkungen
	Ausgabedatum	**Geändert**

Änderungshinweise		
Abschnitt	**Geändertes Element**	**Anmerkungen**
	Ersetzt	**Geändert**
	Überarbeitungsdatum	**Geändert**
2.2	Zusätzliche Sätze	**Geändert**

Abkürzungen und Akronyme:	
REACH	Verordnung zur Registrierung, Bewertung, Zulassung und Beschränkung chemischer Stoffe, Verordnung (EG) Nr. 1907/2006
TRGS	Technische Regeln für Gefahrstoffe
WGK	Wassergefährdungsklasse
IOELV	Arbeitsplatz-Richtgrenzwerte
CLP	Verordnung zur Einstufung, Kennzeichnung und Verpackung; Verordnung (EG) Nr. 1272/2008
ACGIH	American Conference of Governmental Industrial Hygienists
ADN	Europäisches Übereinkommen über die internationale Beförderung gefährlicher Güter auf Binnenwasserstraßen
ADR	Europäisches Übereinkommen über die internationale Beförderung gefährlicher Güter auf der Straße
ATE	Schätzwert der akuten Toxizität
BKF	Biokonzentrationsfaktor
BLV	Biologischer Grenzwert
BOD	Biochemischer Sauerstoffbedarf (BSB)
CAS-Nr.	Chemical Abstracts Service - Nummer
COD	Chemischer Sauerstoffbedarf (CSB)
CSA	Stoffsicherheitsbeurteilung
DMEL	Abgeleitete Expositionshöhe mit minimaler Beeinträchtigung
DNEL	Abgeleitete Expositionshöhe ohne Beeinträchtigung
EG-Nr.	Europäische Gemeinschaft Nummer
EC50	Mittlere effektive Konzentration
ED	Endokriner Disruptor
EN	Europäische Norm
EAK	Europäischer Abfallkatalog
IARC	Internationale Agentur für Krebsforschung
IATA	Verband für den internationalen Lufttransport
IMDG	Gefahrgutvorschriften für den internationalen Seetransport
LC50	Für 50 % einer Prüfpopulation tödliche Konzentration
LD50	Für 50 % einer Prüfpopulation tödliche Dosis (mediane letale Dosis)
LOAEL	Niedrigste Dosis mit beobachtbarer schädlicher Wirkung
Log Kow	Verteilungskoeffizient n-Oktanol/Wasser (Log Kow)
Log Pow	Verteilungskoeffizient n-Oktanol/Wasser (Log Pow)
MAK	Maximale Arbeitsplatz-Konzentration
NOAEC	Konzentration ohne beobachtbare schädliche Wirkung

Abkürzungen und Akronyme:	
NOAEL	Dosis ohne beobachtbare schädliche Wirkung
NOEC	Höchste geprüfte Konzentration ohne beobachtete schädliche Wirkung
N.A.G.	Nicht Anderweitig Genannt
OECD	Organisation für wirtschaftliche Zusammenarbeit und Entwicklung
AGW	Arbeitsplatzgrenzwert
OSHA	Bundesagentur für Sicherheit und Gesundheitsschutz am Arbeitsplatz der Vereinigten Staaten
PBT	Persistenter, bioakkumulierbarer und toxischer Stoff
PNEC	Abgeschätzte Nicht-Effekt-Konzentration
PSA	Persönliche Schutzausrüstung
RID	Ordnung für die internationale Eisenbahnbeförderung gefährlicher Güter
SDB	Sicherheitsdatenblatt
STP	Kläranlage
TF	Technische Funktion
ThSB	Theoretischer Sauerstoffbedarf (ThSB)
TLM	Median Toleranzgrenze
TWA	Zeitlich gewichteter Mittelwert
VOC	Flüchtige organische Verbindungen
vPvB	Sehr persistent und sehr bioakkumulierbar
UFI	Eindeutiger Rezepturidentifikator

Schulungshinweise : Als normaler Gebrauch dieses Produktes gilt eizig und allein der auf der Verpackung vermerkte Gebrauch. Die Verwendungshinweise sorgfältig lesen und beachten. Die Anwendungshinweise beachten (siehe Technisches Datenblatt). Sicherheitsmaßnahmen beachten. Hinweise auf dem Etikett beachten. Alle nationalen/lokalen Vorschriften beachten.

Sonstige Angaben : Technischer Auskunft-Service (s. Abschnitt 1): Erreichbarkeit: Mo - Fr 8:00 - 17:00 Uhr. Registrierung unten https://knauf.com/de-DE/knauf-gips/kontakt-support/technischer-auskunft-service/technischer-auskunft-service-registrierung. Bei privaten Anliegen nutzen Sie bitte unsere umfangreichen digitalen Dienste unter www.knauf-bauherren.de/beratung.

Vollständiger Wortlaut der H- und EUH-Sätze:	
Acute Tox. 2 (Dermal)	Akute Toxizität (dermal), Kategorie 2
Acute Tox. 2 (Inhalativ)	Akute Toxizität (inhalativ), Kategorie 2
Acute Tox. 2 (Inhalativ: Staub, Nebel)	Akute Toxizität (inhalativ: Staub, Nebel), Kategorie 2
Acute Tox. 3 (Oral)	Akute Toxizität (oral), Kategorie 3
Acute Tox. 4 (Oral)	Akute Toxizität (oral), Kategorie 4
Aquatic Acute 1	Akut gewässergefährdend, Kategorie 1
Aquatic Chronic 1	Chronisch gewässergefährdend, Kategorie 1
Eye Dam. 1	Schwere Augenschädigung/Augenreizung, Kategorie 1
Eye Irrit. 2	Schwere Augenschädigung/Augenreizung, Kategorie 2
Skin Corr. 1C	Verätzung/Reizung der Haut, Kategorie 1, Unterkategorie 1C
Skin Irrit. 2	Verätzung/Reizung der Haut, Kategorie 2

Vollständiger Wortlaut der H- und EUH-Sätze:	
Skin Sens. 1A	Sensibilisierung der Haut, Kategorie 1A
H301	Giftig bei Verschlucken.
H302	Gesundheitsschädlich bei Verschlucken.
H310	Lebensgefahr bei Hautkontakt.
H314	Verursacht schwere Verätzungen der Haut und schwere Augenschäden.
H315	Verursacht Hautreizungen.
H317	Kann allergische Hautreaktionen verursachen.
H318	Verursacht schwere Augenschäden.
H319	Verursacht schwere Augenreizung.
H330	Lebensgefahr bei Einatmen.
H400	Sehr giftig für Wasserorganismen.
H410	Sehr giftig für Wasserorganismen mit langfristiger Wirkung.
EUH071	Wirkt ätzend auf die Atemwege.
EUH208	Enthält Reaktionsmasse aus 5-Chlor-2-methyl-2H-isothiazol-3-on und 2-Methyl-2H-isothiazol-3-on (3:1), 1,2-Benzisothiazol-3(2H)-on; 1,2-Benzisothiazolin-3-on. Kann allergische Reaktionen hervorrufen.
EUH210	Sicherheitsdatenblatt auf Anfrage erhältlich.

KNAUF SDS EU (REACH Annex II)

Diese Informationen basieren auf unserem aktuellen Wissen und sollen das Produkt nur im Hinblick auf Gesundheit, Sicherheit und Umweltbedingungen beschreiben. Sie dürfen also nicht als Garantie für spezifische Eigenschaften des Produktes ausgelegt werden.

Gemeinschaft Emissionskontrollierte Verlegewerkstoffe, Klebstoffe und Bauprodukte e.V.

GEV EMICODE®

Lizenzerteilung zur Führung des EMICODE

Lizenzierungs-Nummer:	13856/23.02.15
Für den Artikel	KNAUF ATON SPERRGRUND
der Firma	Knauf Gips KG
wird auf Antrag vom	03.08.2021

unter Bezugnahme auf die Einstufung gemäß den nach § 10 der GEV-Zeichensatzung festgelegten Richtlinien

namens der Gemeinschaft Emissionskontrollierte Verlegewerkstoffe, Klebstoffe und Bauprodukte e.V. für den oben genannten Artikel nach § 5 Abs. 4 der GEV-Zeichensatzung die Lizenz zur Führung des GEV-Zeichens

GEV-EMICODE® EC 1 PLUS sehr emissionsarm

erteilt. Damit erfüllt dieser Artikel die rückseitig aufgeführten Kriterien.
Die Firma ist ordentliches Mitglied der GEV.

Der Geschäftsführer
Gemeinschaft Emissionskontrollierte Verlegewerkstoffe,
Klebstoffe und Bauprodukte e.V.
Völklinger Straße 4 · D-40219 Düsseldorf

OM116 04.08.2021
gültig bis 04.08.2026

Hinweise zu den Voraussetzungen über die Vergabe der Lizenz für den EMICODE

Das gemäß vorseitiger Lizenz eingestufte Produkt hat nach der Satzung und den Richtlinien des Technischen Beirats der GEV u.a. den folgenden Kriterien zu genügen:

- Das Produkt entspricht allen gesetzlichen Bestimmungen, insbesondere denen des Chemikalienrechtes und seiner Verordnungen.
- Das Produkt ist nach der Definition der TRGS 610 lösemittelfrei, sofern es sich nicht um ein Oberflächenprodukt handelt. Soweit es einer Produktgruppe nach GISCODE zuzuordnen ist, wird diese angegeben.
- Für das Produkt wird ein Sicherheitsdatenblatt nach lokalem Recht in der jeweils aktuellen Fassung erstellt.
- Krebserregende, erbgutverändernde oder fruchtschädigende Stoffe der Klassen 1A und 1B werden dem Produkt bei der Herstellung nicht zugesetzt.
- Die Prüfung des Produktes erfolgt nach der definierten „GEV-Prüfmethode“. Die VOC-Bestimmung wird dabei in einer Prüfkammer nach dem Tenax-Thermodesorptions-Verfahren mit nachgeschalteter GC/MS-Analyse durchgeführt.
- Die Einstufung in EMICODE-Klassen erfolgt entsprechend den nachstehenden Bezeichnungen und TVOC/TSVOC-Konzentrationsbereichen. Zur Produktkennzeichnung ist die zutreffende EMICODE-Klasse zu verwenden:

1) Verlegewerkstoffe, Klebstoffe und Bauprodukte

Parameter	EC 1 PLUS	EC 1	EC 2
	max. zulässige Konzentration [µg/m³]		
TVOC nach 3 Tagen	≤ 750	≤ 1000	≤ 3000
TVOC nach 28 Tagen	≤ 60	≤ 100	≤ 300
TSVOC nach 28 Tagen	≤ 40	≤ 50	≤ 100
R-Wert basierend auf AgBB-NIK-Werten nach 28 Tagen	1	-	-
Summe der nicht bewertbaren VOC	≤ 40	-	-
Formaldehyd nach 3 Tagen	≤ 50	≤ 50	≤ 50
Acetaldehyd nach 3 Tagen	≤ 50	≤ 50	≤ 50
Summe von Form- und Acetaldehyd	≤ 0,05 ppm	≤ 0,05 ppm	≤ 0,05 ppm
Summe von flüchtigen K1A/K1B Stoffen nach 3 Tagen	≤ 10	≤ 10	≤ 10
Jeder flüchtige K1A/K1B Stoff nach 28 Tagen	≤ 1	≤ 1	≤ 1

2) Oberflächenbehandlungsmittel für Parkett, mineralische Böden und elastische Bodenbeläge

Parameter	EC 1 PLUS	EC 1	EC 2
	max. zulässige Konzentration [µg/m³]		
Summe TVOC + TSVOC nach 28 Tagen	≤ 100 davon max. 40 SVOC	≤ 150 davon max. 50 SVOC	≤ 450 davon max. 100 SVOC
Formaldehyd nach 3 Tagen	≤ 50	≤ 50	≤ 50
Acetaldehyd nach 3 Tagen	≤ 50	≤ 50	≤ 50
Jeder flüchtige K1A/K1B Stoff nach 3 Tagen	≤ 10	≤ 10	≤ 10
Jeder flüchtige K1A/K1B Stoff nach 28 Tagen	≤ 1	≤ 1	≤ 1



valid until
07.06.2027

EPD-DBC-20220146-IBF1-EN

Primer

Declared Products

- *Aton-Sperrgrund*
- *Aufbrennsperre*
- *Betokontakt*
- *Casiol Grund, white*
- *Grundol*
- *Quartzgrund Pro, white*
- *Raumklima Grundierung, white*
- *Spraykontakt*

www.knauf.com

Build on us.

ENVIRONMENTAL PRODUCT DECLARATION

as per *ISO 14025* and *EN 15804+A2*

Owner of the Declaration	DBC, EFCC, FEICA, IVK
Programme holder	Institut Bauen und Umwelt e.V. (IBU)
Publisher	Institut Bauen und Umwelt e.V. (IBU)
Declaration number	EPD-DBC-20220146-IBF1-EN
Issue date	08.06.2022
Valid to	07.06.2027

Dispersion-based products, group 1

DBC - Deutsche Bauchemie e.V.

EFCC - European Federation for Construction Chemicals

FEICA - Association of the European Adhesive and Sealant Industry

IVK - Industrieverband Klebstoffe e.V.

Institut Bauen und Umwelt e.V.

www.ibu-epd.com | https://epd-online.com

ECO PLATFORM EPD VERIFIED



1. General Information

DBC - Deutsche Bauchemie e.V.
EFCC - European Federation for Construction Chemicals
FEICA - Association of the European Adhesive and Sealant Industry
IVK - Industrieverband Klebstoffe e.V.

Dispersion-based products, group 1

Programme holder
IBU – Institut Bauen und Umwelt e.V.
Hegelplatz 1
10117 Berlin
Germany

Owner of the declaration
DBC, Mainzer Landstr. 55, D-60329 Frankfurt a.M.
EFCC, 172 Boulevard du Triomphe, B-1160 Brussels
FEICA, Rue Belliard 40, B-1040 Brussels
IVK, Völklingerstr. 4, D-40219 Düsseldorf

Declaration number
EPD-DBC-20220146-IBF1-EN

Declared product / declared unit
1 kg / 1 kg; density 1,000 - 1,500 kg/m³

This declaration is based on the product category rules:
Dispersion adhesives and primers for floor coverings, 01.2019
(PCR checked and approved by the SVR)

Scope:
This verified EPD entitles the holder to bear the symbol of the Institut Bauen und Umwelt e.V. It exclusively applies to products produced in Europe and applies to a period of five years from the date of issue. This EPD may be used by members of DBC, EFCC, FEICA and IVK and their members provided it has been proven that the respective product can be represented by this EPD. For this purpose, a guideline is available at the secretariats of the four associations. The members of the associations are listed on their respective websites.

Issue date
08.06.2022

Valid to
07.06.2027

The owner of the declaration shall be liable for the underlying information and evidence; the IBU shall not be liable with respect to manufacturer information, life cycle assessment data and evidences.

The EPD was created according to the specifications of *EN 15804+A2*. In the following, the standard will be simplified as *EN 15804*.

Verification

The standard *EN 15804* serves as the core PCR
Independent verification of the declaration and data according to *ISO 14025:2011*
☐ internally ☒ externally

Dipl. Ing. Hans Peters
(chairman of Institut Bauen und Umwelt e.V.)

Dr. Alexander Röder
(Managing Director Institut Bauen und Umwelt e.V.))

Matthias Schulz
(Independent verifier)

2. Product

2.1 Product description/Product definition

This EPD comprises dispersion-based products with a Volatile Organic Compound (VOC) content ≤1 % (VOC definition according to *Decopaint Directive*). The products typically consist of organic binding agents based on synthetic and/or natural resins, mineral fillers such as chalk as well as water and smaller volumes of auxiliaries (thickening agents, defoaming agents, surface-active agents, preservatives etc.). They dry physically through evaporation of the water contained therein. They comply with manifold, often specific, functions in the construction, furnishing and repair of buildings. Using dispersion-based products decisively improves the fitness for use of structures and extends their life expectancy. The product displaying the highest environmental impacts within the class of dispersion-based products considered was used as a representative product for calculating the Life Cycle Assessment results (worst-case approach).

For the placing on the market in the European Union/European Free Trade Association (EU/EFTA) with the exception of Switzerland) products falling under the Regulation (EU) No 305/2011 (*CPR*) need a Declaration of Performance taking into consideration either the relevant harmonised European standard or

the European Technical Assessment and the CE marking. For the application and use of the products the respective national provisions apply.

2.2 Application

Dispersion-based products are used for the following applications:

Module 1: Dispersion adhesives, fixatives, precoatings and primers for floor coverings and parquet flooring
Adhesives for, e.g. tufted carpets with various backings, woven textile coverings, fibre-bonded and natural fibre coverings, resilient coverings (PVC, rubber, PVC-free luxury vinyl tiles), linoleum, insulating bases and underlays, parquet, laminate and wood blocks on surfaces ready for laying. The products are suitable for normal wear in residential and commercial areas, also on heated floor constructions.

Module 2: Dispersion-based tile adhesive
Products for bonding ceramic tiles and paving as well as natural stone for internal and external installations on walls, floors and ceilings

Module 3: Dispersion-based adhesives and sealants
As structural adhesives and sealants: ·structural and repair adhesives, dispersion filler compounds, joint sealants

Module 4: Dispersion-based products for waterproofing of buildings
Products for waterproofing floors and/or walls in wet rooms inside buildings

Module 5: Dispersion-based primers and bonding agents for concrete and floor screeds
Products to improve the adhesion of e.g. self-levelling compounds or repair mortars on absorbent cement and calcium sulphate screeds, concrete, dry construction boards

Module 6: Dispersion-based products for surface protection of concrete
To increase the durability of concrete and reinforced steel structures as well as for new concrete and for maintenance and repair work (for areas without vehicle traffic)

Module 7: Dispersion-based primers and barrier coatings
Products to protect a substrate from e.g. the immersion of water, thus preventing degradation, corrosion or damage

2.3 Technical Data

The density of the products is between 1,00 and 1,50 g/cm³, other relevant technical data can be found in the manufacturer’s technical documentation.

Module 1: Dispersion adhesives, fixatives, precoatings and primers for floor coverings and parquet flooring
Dispersion adhesives for floor coverings have to comply with the requirements of the *EN ISO 22636*. The mechanical requirements of *EN ISO 22636* don’t apply to fixatives; their strengths are lower in accordance with their specifications. The performance characteristics of precoatings and primers are subject to the manufacturer's technical documentation/declaration of performance. Dispersion adhesives for parquet: The test procedures and requirements of the *EN ISO 17178* have to be fulfilled.

Module 2: Dispersion-based tile adhesive
The requirements on essential characteristics according to *EN 12004*, must be maintained. These are:
Tensile adhesion strength after dry storage (*EN 12004-2*)
-Tensile adhesion strength after water immersion (*EN 12004-2*)
-Tensile adhesion strength after heat ageing (*EN 12004*)
-Tensile adhesion strength after freeze/thaw cycles (*EN 12004-2*)
-Open time: Tensile strength (*EN 12004-2*)
Further essential characteristics in accordance with the manufacturer's technical documentation

Module 3: Dispersion-based adhesives and sealants
Performance characteristics in accordance with the manufacturer's technical documentation/declaration of performance

Module 4: Dispersion-based products for waterproofing of buildings
The minimum requirement of *EAD 030352-00-0503* - Liquid applied watertight covering kits for wet room floors and/or walls- must be maintained. The essential characteristics are to be specified in accordance with the European technical assessment (ETA, specification no.).

Module 5: Dispersion-based primers and bonding agents for concrete and floor screeds
Performance characteristics in accordance with the manufacturer's technical documentation

Module 6: Dispersion-based products for surface protection of concrete
The requirements on essential characteristics for all intended uses in accordance with *EN 1504-2*, Tables 1 and 5, must be maintained. These are:
- Permeability to CO_2 (*EN 1062-6*)
- Water vapour permeability (*EN ISO 7783-1/-2*)
- Capillary absorption and permeability to water (*EN 1062-3*)
- Adhesion strength by pull-off test (*EN 1542*)

Further essential characteristics in accordance with the manufacturer's technical documentation/declaration of performance

Module 7: Dispersion-based primers and barrier coatings
The requirements of the *Decopaint Directive* must be maintained.
Essential characteristics in accordance with the manufacturer's technical documentation/declaration of performance.

2.4 Delivery status

Liquid or pasty in containers made of plastic or metal. Typical container sizes contain 1 to 30 kg, usually 10 to 20 kg of product on pallets. For larger applications,

vats with approx. volumes of 200 kg (litres) or IBCs (intermediate bulk containers) with a capacity of 1 tonne (m³) or more are also used. A plastic container was modelled for the Life Cycle Assessment.

2.5 Base materials/Ancillary materials

Dispersion-based products usually comprise at least one synthetic resin dispersion, natural or synthetic resins dispersed in water, mineral fillers (e.g. chalk) and/or pigments. Auxiliaries such as thickening agents, defoaming agents, surface-active and dispersing agents as well as preservatives are used to fine-tune the product features. **Typically**, the products covered by this EPD contain the following range of base materials and auxiliaries (% by mass):

- Synthetic polymer dispersion (solids portion): 5 - 65
- Natural resins, natural resin derivatives: 0 - 25
- Mineral fillers: 0 - 60
- Pigments: 0 - 35
- Water: 15 - 95
- Auxiliaries: 1 - 5
- Thickening agents: < 3
- Dispersing agents/Emulsifying agents: < 2
- Wetting agent: 2
- Other: 0 - 2
- VOC according to *Decopaint Directive*: <1 % **(mandatory)**

These ranges are average values and the composition of products complying with the EPD can deviate from these concentration levels in individual cases. More detailed information is available in the respective manufacturer's documentation (e.g. product data sheets).

Note: For companies to declare their products within the scope of this EPD it is not sufficient to simply comply with the product composition shown above. The application of this EPD is only possible for member companies of DBC, EFCC, FEICA, and IVK member associations and only for specific formulations with a total score below the declared maximum score for a product group according to the associated guidance document.

1. substances from the "Candidate List of Substances of Very High Concern for Authorisation" (SVHC)

If this product contains substances listed in the *candidate list* (latest version) exceeding 0.1 percentage by mass, the relevant information can be found in the safety data sheet of the relevant product covered by this model EPD.

2. CMR substances in categories 1A and 1B

If this product contains other carcinogenic, mutagenic, reprotoxic (CMR) substances in categories 1A or 1B which are not on the *candidate list*, exceeding 0.1 percentage by mass, the relevant information can be found in the safety data sheet of the relevant product covered by this model EPD.

3. Biocide products added to the construction product

If this construction product contains biocide products, the active substances, information on the concentration and/or concentration range, the product type together with information on their hazardous properties are listed in the safety data sheet of the respective product.

2.6 Manufacture

Dispersion-based products are usually mixed discontinuously in batch mode, i.e. in individual batches or a series of individual batches, and filled into the delivery containers.

2.7 Environment and health during manufacturing

As a general rule, no particular environmental or health protection measures other than those specified by law are necessary.

2.8 Product processing/Installation

Dispersion based products are processed on site using suitable tools, usually by hand. The products are applied by trowelling/knife-coating, painting, rolling or spraying. Precautions for safe handling and storage (e.g. air exchange, exhaust ventilation, personal protective measures, conditions for safe storage) must be observed in accordance with the information on the safety data sheet.

Depending on the application and product specifications, between 50 and 1,500 g/m² are applied.

2.9 Packaging

A detailed description of packaging is provided in section 2.4. Empty containers and clean foils can be recycled.

2.10 Condition of use

During the use phase, dispersion-based products are existent as hardened film. They are long-lasting products which protect our buildings in the form of adhesives, primers, coatings or sealants as well as make an essential contribution towards their appearance, function and sustainability.

2.11 Environment and health during use

Option 1 – Products for applications outside indoor areas with permanent stays by people

No risks are known for water, air and soil if the products are used as designated.

Option 2 – Products for applications inside indoor areas with permanent stays by people

When used in indoor areas with permanent stays by people, evidence of the emission performance of construction products in contact with indoor air must be submitted according to national requirements (see chapter 7). No further influences by emissions on the environment and health are known.

2.12 Reference service life

Dispersion-based products fulfill manifold, often specific, functions in the construction or refurbishment of building structures. They decisively improve the usability of building structures and significantly extend their original service lives. The anticipated reference service life depends on the specific installation situation and the exposure associated with the product. It can be influenced by weathering as well as mechanical or chemical load.

2.13 Extraordinary effects

Fire

In terms of the volumes applied, dispersion based products have no or only a marginal influence on the fire performance characteristics of the building structure in which they have been installed.

Water
Dispersion-based products are water-resistant only to a certain degree and their strength can deteriorate when exposed to water for longer periods (of time); detaching from the surface is possible in a worst-case scenario. The components of dispersion-based products are not hazardous to water or only slightly hazardous to water. Owing to the overall low volumes of dispersion-based products used on buildings, no relevant contribution towards environmental damage can be anticipated by buildings featuring dispersion-based products in the event of extraordinary exposure to water.

Mechanical destruction
The mechanical destruction of dispersion-based products does not lead to any decomposition products which are harmful to the environment or health.

2.14 Re-use phase
According to present knowledge, no environmentally hazardous effects in terms of landfilling are to be generally anticipated through dismantling and recycling components to which dispersion-based products have been applied and on which they have dried.

2.15 Disposal
The low amounts of a dispersion-based product applied to a construction product will not interfere with the disposal/recycling of this.
Hardened product residue mechanically removed from substrates must be disposed of as commercial/construction waste. The following waste codes according to the European List of Waste (*2000/532/EC*) can apply:
Hardened product residue:
080112 Paint and varnish waste with the exception of that covered by 08 01 11
080410 Adhesive and sealant compound waste with the exception of that covered by 08 04 09

2.16 Further information
More information is available on the manufacturer's product or safety data sheets and is available on the manufacturer's websites or on request. Valuable technical information is also available on the associations' websites.

3. LCA: Calculation rules

3.1 Declared Unit
This EPD refers to the declared unit of 1 kg of dispersion-based product, group 1; applied into the building with a density of 1,000 - 1,500 kg/m³ in accordance with the *IBU PCR* part B for dispersion adhesives and primers for floor coverings.
The results of the Life Cycle Assessment provided in this declaration have been selected from the product with the highest environmental impact (worst-case scenario).
Depending on the application, a corresponding conversion factor such as the density to convert volumetric use to mass must be taken into consideration.

The Declaration type is according to *EN 15804*: Cradle to gate with options, modules C1–C3, and module D (A1–A3, C, D) and additional modules (A4-A5).

Declared unit

Name	Value	Unit
Declared unit	1	kg
Gross density	1,000-1,500	kg/m^3

3.2 System boundary
Modules A1, A2 and A3 are taken into consideration in the LCA:
- A1 Production of preliminary products
- A2 Transport to the plant
- A3 Production incl. provision of energy, production of packaging as well as auxiliaries and consumables and waste treatment
- A4 Transport to site
- A5 Installation, product applied into the building during A5 phase operations and packaging disposal.

The end of life for the packaging material considered is described below:
-Incineration, for materials like plastic and wood.
-C1-C2-C3-D
The building deconstruction (demolition process) takes place in the C1 module which considers energy production and consumption in terms of diesel and all the emissions connected with the fuel-burning process to run the machines. After the demolition, the product is transported to the end-of-life processing (C2 module) where all the impacts related to the transport processes are considered. For precautionary principle and as a worst-case scenario, thermal treatment is the only end of life scenario considered. This is modelled by the incineration process (module C3) where the product ends its life cycle.
Module D accounts for potential benefits that are beyond the defined system boundaries. Credits are generated during the incineration of wastes and related electricity produced that are occurring in the A5 module.

3.3 Estimates and assumptions
For this EPD formulation and production data defined and collected by FEICA were considered. Production waste was assumed to be disposed of by incineration without credits as a worst-case.
An average of plastic containers and wooden pallets was considered in the LCA.

3.4 Cut-off criteria
All raw materials submitted for the formulations and production data were taken into consideration.
The manufacture of machinery, plant and other infrastructure required for the production of the products under review was not taken into consideration in the LCA.
Transport of packaging materials is excluded.

3.5 Background data
Data from the *GaBi* database SP40 (2020) was used as background data.

3.6 Data quality

Representative products were applied for this EPD and the product in the group displaying the highest environmental impact was selected for calculating the LCA results. The background datasets used are less than 4 years old.
Production data and packaging are based on details provided by the manufacturer. The formulation used for evaluation refers to a specific product.
The data quality of the background data is considered to be good.

3.7 Period under review

Representative formulations are valid for 2021.

3.8 Allocation

Mass allocation has been applied when primary data have been used and implemented into the LCA model.

3.9 Comparability

Basically, a comparison or an evaluation of EPD data is only possible if all the data sets to be compared were created according to *EN 15804* and the building context, respectively the product-specific characteristics of performance, are taken into account.

The *GaBi* database SP40 (2020) was used.

4. LCA: Scenarios and additional technical information

Characteristic product properties
Information on biogenic Carbon
The packaging material contains biogenic carbon content which is presented below.

Information on describing the biogenic Carbon Content at factory gate

Name	Value	Unit
Biogenic carbon content in product	-	kg C
Biogenic carbon content in accompanying packaging	0.016	kg C

For the preparation of building life cycle assessments, it must be taken into account that in module A5 (installation in the building) the biogenic amount of CO_2 (0.016 kg C *3.67 = 0.059 kg CO_2-eq.) of the packaging bound in module A1-A3 is mathematically booked out.

Transport to the building site (A4)

Name	Value	Unit
Transport distance	1000	km
Gross weight	34 - 40	t
Payload capacity	27	t

Installation into the building (A5)

Name	Value	Unit
Other resources for packaging material	0.067	kg
Material loss	0.01	kg

Material loss regards the amount of product not used during the application phase into the building. This amount is 1% of the product, impacts related to the production of this part are charged to the A5 module. This percentage is considered as waste to disposal and impacts of its end of life have been considered in the LCA model and declared in A5.

End of life (C1-C3)

Name	Value	Unit
Collected as mixed construction waste	1	kg
Incineration	1	kg

5. LCA: Results

DESCRIPTION OF THE SYSTEM BOUNDARY (X = INCLUDED IN LCA; ND = MODULE OR INDICATOR NOT DECLARED; MNR = MODULE NOT RELEVANT)

PRODUCT STAGE			CONSTRUCTION PROCESS STAGE		USE STAGE							END OF LIFE STAGE				BENEFITS AND LOADS BEYOND THE SYSTEM BOUNDARIES
Raw material supply	Transport	Manufacturing	Transport from the gate to the site	Assembly	Use	Maintenance	Repair	Replacement	Refurbishment	Operational energy use	Operational water use	De-construction demolition	Transport	Waste processing	Disposal	Reuse-Recovery-Recycling-potential
A1	A2	A3	A4	A5	B1	B2	B3	B4	B5	B6	B7	C1	C2	C3	C4	D
X	X	X	X	X	ND	ND	MNR	MNR	MNR	ND	ND	X	X	X	ND	X

RESULTS OF THE LCA - ENVIRONMENTAL IMPACT according to EN 15804+A2: 1 kg of dispersion-based product, group 1

Core Indicator	Unit	A1-A3	A4	A5	C1	C2	C3	D
GWP-total	[kg CO_2-Eq.]	1.32E+0	5.11E-2	1.73E-1	2.79E-4	1.24E-2	9.45E-1	-3.98E-1
GWP-fossil	[kg CO_2-Eq.]	1.36E+0	5.06E-2	8.81E-2	2.66E-4	1.18E-2	4.29E-1	-3.97E-1
GWP-biogenic	[kg CO_2-Eq.]	-5.05E-2	1.48E-4	8.53E-2	1.24E-5	5.42E-4	5.15E-1	-8.96E-4
GWP-luluc	[kg CO_2-Eq.]	4.52E-4	4.10E-4	6.04E-6	6.39E-9	2.79E-7	3.50E-5	-2.51E-4
ODP	[kg CFC11-Eq.]	3.00E-14	6.08E-18	3.18E-16	2.84E-20	1.24E-18	3.02E-16	-3.72E-15
AP	[mol H^+-Eq.]	4.90E-3	1.52E-4	7.29E-5	3.60E-6	3.73E-5	5.25E-4	-5.26E-4
EP-freshwater	[kg P-Eq.]	2.65E-5	1.54E-7	2.68E-7	5.75E-11	2.51E-9	1.04E-7	-4.62E-7
EP-marine	[kg N-Eq.]	1.03E-3	6.75E-5	1.75E-5	1.63E-6	1.72E-5	2.01E-4	-1.39E-4
EP-terrestrial	[mol N-Eq.]	1.24E-2	7.56E-4	2.36E-4	1.79E-5	1.89E-4	2.52E-3	-1.49E-3
POCP	[kg NMVOC-Eq.]	3.63E-3	1.33E-4	5.62E-5	4.91E-6	3.39E-5	5.22E-4	-4.02E-4
ADPE	[kg Sb-Eq.]	6.50E-7	3.63E-9	6.77E-9	8.06E-12	3.52E-10	4.62E-9	-6.06E-8
ADPF	[MJ]	3.30E+1	6.73E-1	3.61E-1	3.81E-3	1.66E-1	5.52E-1	-6.70E+0
WDP	[m^3 world-Eq deprived]	4.60E-1	4.52E-4	2.10E-2	5.27E-7	2.30E-5	1.57E-1	-3.70E-2

Caption	GWP = Global warming potential; ODP = Depletion potential of the stratospheric ozone layer; AP = Acidification potential of land and water; EP = Eutrophication potential; POCP = Formation potential of tropospheric ozone photochemical oxidants; ADPE = Abiotic depletion potential for non-fossil resources; ADPF = Abiotic depletion potential for fossil resources; WDP = Water (user) deprivation potential

RESULTS OF THE LCA - INDICATORS TO DESCRIBE RESOURCE USE according to EN 15804+A2: 1 kg of dispersion-based product, group 1

Indicator	Unit	A1-A3	A4	A5	C1	C2	C3	D
PERE	[MJ]	4.66E+0	3.79E-2	6.43E-1	1.20E-5	5.25E-4	9.36E-2	-1.32E+0
PERM	[MJ]	5.85E-1	0.00E+0	-5.85E-1	0.00E+0	0.00E+0	0.00E+0	0.00E+0
PERT	[MJ]	5.25E+0	3.79E-2	5.83E-2	1.20E-5	5.25E-4	9.36E-2	-1.32E+0
PENRE	[MJ]	1.78E+1	6.74E-1	1.31E+0	3.81E-3	1.67E-1	1.49E+1	-6.70E+0
PENRM	[MJ]	1.53E+1	0.00E+0	-9.53E-1	0.00E+0	0.00E+0	-1.43E+1	0.00E+0
PENRT	[MJ]	3.30E+1	6.74E-1	3.62E-1	3.81E-3	1.67E-1	5.52E-1	-6.70E+0
SM	[kg]	0.00E+0	0.00E+0	0.00E+0	0.00E+0	0.00E+0	0.00E+0	0.00E+0
RSF	[MJ]	0.00E+0	0.00E+0	0.00E+0	0.00E+0	0.00E+0	0.00E+0	0.00E+0
NRSF	[MJ]	0.00E+0	0.00E+0	0.00E+0	0.00E+0	0.00E+0	0.00E+0	0.00E+0
FW	[m^3]	1.19E-2	4.38E-5	5.03E-4	2.16E-8	9.41E-7	3.70E-3	-1.53E-3

Caption	PERE = Use of renewable primary energy excluding renewable primary energy resources used as raw materials; PERM = Use of renewable primary energy resources used as raw materials; PERT = Total use of renewable primary energy resources; PENRE = Use of non-renewable primary energy excluding non-renewable primary energy resources used as raw materials; PENRM = Use of non-renewable primary energy resources used as raw materials; PENRT = Total use of non-renewable primary energy resources; SM = Use of secondary material; RSF = Use of renewable secondary fuels; NRSF = Use of non-renewable secondary fuels; FW = Use of net fresh water

RESULTS OF THE LCA – WASTE CATEGORIES AND OUTPUT FLOWS according to EN 15804+A2: 1 kg of dispersion-based product, group 1

Indicator	Unit	A1-A3	A4	A5	C1	C2	C3	D
HWD	[kg]	8.74E-9	3.14E-8	1.23E-10	3.70E-13	1.62E-11	1.77E-9	-2.66E-9
NHWD	[kg]	1.30E-2	1.03E-4	2.35E-3	3.90E-7	1.70E-5	1.36E-1	-2.94E-3
RWD	[kg]	6.56E-4	8.34E-7	8.31E-6	4.09E-9	1.79E-7	2.51E-5	-4.51E-4
CRU	[kg]	0.00E+0	0.00E+0	0.00E+0	0.00E+0	0.00E+0	0.00E+0	0.00E+0
MFR	[kg]	0.00E+0	0.00E+0	0.00E+0	0.00E+0	0.00E+0	0.00E+0	0.00E+0
MER	[kg]	0.00E+0	0.00E+0	0.00E+0	0.00E+0	0.00E+0	0.00E+0	0.00E+0
EEE	[MJ]	0.00E+0	0.00E+0	2.77E-1	0.00E+0	0.00E+0	0.00E+0	0.00E+0
EET	[MJ]	0.00E+0	0.00E+0	5.01E-1	0.00E+0	0.00E+0	0.00E+0	0.00E+0

Caption	HWD = Hazardous waste disposed; NHWD = Non-hazardous waste disposed; RWD = Radioactive waste disposed; CRU = Components for re-use; MFR = Materials for recycling; MER = Materials for energy recovery; EEE = Exported electrical energy; EET = Exported thermal energy

RESULTS OF THE LCA – additional impact categories according to EN 15804+A2-optional: 1 kg of dispersion-based product, group 1

Indicator	Unit	A1-A3	A4	A5	C1	C2	C3	D
PM	[Disease Incidence]	ND	ND	ND	ND	ND	ND	ND
IRP	[kBq U235-Eq.]	ND	ND	ND	ND	ND	ND	ND
ETP-fw	[CTUe]	ND	ND	ND	ND	ND	ND	ND
HTP-c	[CTUh]	ND	ND	ND	ND	ND	ND	ND
HTP-nc	[CTUh]	ND	ND	ND	ND	ND	ND	ND
SQP	[-]	ND	ND	ND	ND	ND	ND	ND

Caption	PM = Potential incidence of disease due to PM emissions; IR = Potential Human exposure efficiency relative to U235; ETP-fw = Potential comparative Toxic Unit for ecosystems; HTP-c = Potential comparative Toxic Unit for humans (cancerogenic); HTP-nc = Potential comparative Toxic Unit for humans (not cancerogenic); SQP = Potential soil quality index

Potential Human exposure efficiency relative to U235, Disclaimer 1 – This impact category deals mainly with the eventual impact of low dose ionizing radiation on human health of the nuclear fuel cycle. It does not consider effects due to possible nuclear accidents, occupational exposure nor radioactive waste disposal in underground facilities. Potential ionizing radiation from the soil, radon and (from) some construction materials is also not measured by this indicator.

ADP minerals & metals, ADP fossil, WDP, ETF-fw, HTP-c, HTP-nc, SQP, Disclaimer 2 – The results of this environmental impact indicator shall be used with care as the uncertainties on these results are high or as there is limited experience with the indicator.

Additional environmental impact indicators (suggested by *EN15804*, table 4) are not declared in the EPD. The results of this environmental impact indicator shall be used with care as the uncertainties on these results are high and as there is limited experience with the indicator (see ILCD classification in *EN 15804*, table 5). For this reason, results based on these indicators are not considered suitable for a decision-making process and are thus not declared in the EPD.

6. LCA: Interpretation

The majority of impacts are associated with the production phase (A1-A3). The most significant contribution to the production phase impacts is the upstream production of raw materials as the main driver. Another contributor in the production phase, in the category of Photochemical ozone formation (POCP), is the plastic used as a packaging material. Emissions associated with the manufacturing of products also have some influence on Ozone Depletion Potential (ODP) in the production phase. In all EPDs, CO_2 is the most important contributor to Global Warming Potential (GWP). For the Acidification Potential (AP), NOx and SO_2 contribute the largest share.
The majority of life cycle energy consumption takes place during the production phase (A1-A3). Significant contributions to Primary Energy Demand – Non-renewable (PENRT) come from the energy resources used in the production of raw materials. The largest contributor to Primary Energy Demand – Renewable (PERT) impacts comes from the consumption of renewable energy resources required for the generation and supply of electricity. It should be noted that Primary Energy Demand – Renewable (PERT) generally represents a small percentage of the production phase primary energy demand with the bulk of the demand coming from non-renewable energy resources.
Transportation to the construction site (A4) and the installation process (A5) make a low contribution to all impacts. Climate change from land-use change is the only indicator influenced by transport processes, due to the diesel production used as fuel because part of this diesel has been produced from bio-based raw materials.
The installation phase influence mainly climate change indicators, due to the impact related to the incineration processes used for packaging waste treatment and residual product treatment (1 % of the total mass).
The end-of-life phases influence climate change indicators, due to the thermal treatment process of the dispersion-based product occurring in the C3 module.

7. Requisite evidence

VOC
Special tests and evidence have not been carried out or provided within the framework of drawing up this Model EPD. Some member states require special documentation on VOC emissions into indoor air for specific areas of application. This documentation, as well as documentation for voluntary VOC labelling, has to be provided separately and is specific for the product in question.

Evidence pertaining to VOC emissions shall show
- either an attestation of compliance with,
- or documentation of test data that are required in any of the existing regulations or in any of the existing voluntary labelling programs for low-emitting products, as far as these

(1) include limits for the parameters TVOC, TSVOC, carcinogens, formaldehyde, acetaldehyde, LCI limits for individual substances (including but not limited to the European list of harmonized LCIs), and the R-value;
(2) base their test methods on *EN 16516*;
(3) perform testing and apply the limits after 28 days of storage in a ventilated test chamber, under the conditions specified in *EN 16516*; some regulations and programs also have limits after 3 days, on top of the 28 days limits;

(4) express the test results as air concentrations in the European Reference Room, as specified in *EN 16516*.

Examples of such regulations are the *Belgian Royal Decree C-2014/24239*, or the *German AgBB/* ABG. Examples of such voluntary labelling programs are *EMICODE*, *Blue Angel* or *Indoor Air Comfort*.

Relevant test results shall be produced either by an *ISO 17025* accredited commercial test lab or by a qualified internal test lab of the manufacturer.
Examples for the applied limits after 28 days of storage in a ventilated test chamber are:

- TVOC: 1000 µg/m³
- TSVOC: 100 µg/m³
- Each carcinogen: 1 µg/m³
- Formaldehyde: 100 µg/m³
- LCI: different per substance involved
- R-value: 1 (meaning that, in total, 100 % of the combined LCI values must not be exceeded).

Informative Annexes (2 tables):
Table 1 shown below is an overview of the most relevant regulations and specifications as of October 2021, as regards requirements after 3 days of storage in a ventilated test chamber.
Table 2 provides an overview of the most relevant regulations and specifications as of October 2021, as regards requirements after 28 days of storage in a ventilated test chamber. Some details may be missing in the table due to lack of space. Values given represent maximum values/limits.

	TVOC µg/m³	Sum of carcinogens. C1A,CA2 µg/m³	Formaldehyde µg/m³	Acetaldehyde µg/m³	Sum of Form- and Acetaldehyde
German AgBB/ABG regulation	10 000	10	-/-	-/-	-/-
Belgian regulation	10 000	10	-/-	-/-	-/-
EMICODE EC1	1 000	10	50	50	50 ppb
EMICODE EC1 *PLUS*	750	10	50	50	50 ppb

	TVOC µg/m³	TSVOC µg/m³	Each carcinogen C1A,CA2 µg/m³	Formalde-hyde µg/m³	Acetalde-hyde µg/m³	LCI	R value	Specials	Sum of non-LCI & non-identified µg/m³
Belgian regulation	1000	100	1	100	200	Belgian list	1	Toluene 300 µg/m³	-/-
French regulations class A+	1000	-/-	-/-	10	200	-/-	-/-	List of 8 VOCs, 4 CMR	-/-
French regulations class A	1500	-/-	-/-	60	300	-/-	-/-	List of 8 VOCs, 4 CMR	-/-
French regulations class B	2000	-/-	-/-	120	400	-/-	-/-	List of 8 VOCs, 4 CMR	-/-
French regulations class C	>2000	-/-	-/-	>120	>400	-/-	-/-	List of 8 VOCs, 4 CMR	-/-
German DIBt/AgBB regulation	1000	100	1	100	300	German AgBB list	1	-/-	100
EMICODE EC1	100	50	1	(after 3 days)	(after 3 days)	-/-	-/-	-/-	-/-
EMICODE EC1 *PLUS*	60	40	1	(after 3 days)	(after 3 days)	German AgBB list	1	-/-	40
Finnish M1, sealants	20	-/-	1	10	300	EU LCI list	-/-	Ammonia, odour	-/-
Finnish M1, adhesives	200 µg/m²h	-/-	5 µg/m²h	50 µg/m²h	300	EU LCI list	-/-	Ammonia, odour	-/-

8. References

EN 1062-3
EN 1062-3:2008-04, Paints and varnishes - Coating materials and coating systems for exterior masonry and concrete - Part 3: Determination of liquid water permeability

EN 1062-6
EN 1062-6:2002-10, Paints and varnishes - Coating materials and coating systems for exterior masonry

and concrete - Part 6: Determination of carbon dioxide permeability

EN 1504-2
EN 1504-2:2004-10, Products and systems for the protection and repair of concrete structures - Definitions, requirements, quality control and evaluation of conformity - Part 2: Surface protection systems for concrete

EN 1542
EN 1542:1999-07, Products and systems for the protection and repair of concrete structures - Test methods - Measurement of bond strength by pull-off

EN ISO 7783-1/-2
EN ISO 7783-1/-2:2019-02, Paints and varnishes - Determination of water-vapour transmission properties - Cup method

EN 12004
EN12004:2012, Adhesives for ceramic tiles

EN 12004-2
EN 12004-2:2017, Adhesives for ceramic tiles - Part 2: Test methods

ISO 14025
DIN EN ISO 14025:2011-10, Environmental labels and declarations — Type III environmental declarations — Principles and procedures

EN 15804
EN 15804:2019+A2+AC, Sustainability of construction works — Environmental Product Declarations — Core rules for the product category of construction products.

EN 16516
EN 16516:2017
Construction products - Assessment of release of dangerous substances - Determination of emissions into indoor air

EN ISO 17025
EN ISO 17025: 2018-03
General requirements for the competence of testing and calibration laboratories

EN ISO 17178
EN ISO 17178:2020, Adhesives - Adhesives for bonding parquet to subfloor - Test methods and minimum requirements

EN ISO 22636
EN ISO 22636:2020, Adhesives - Adhesives for floor coverings - Requirements for mechanical and electrical performance

EAD 030352-00-0503
EAD 030352-00-0503:2019-01, Watertight covering kits for wet room floors and or walls Part 1: Liquid Applied Coverings with or without wearing surface Part 2: Kits based on flexible sheets Part 3: Kits based on inherently watertight boards

(EU) No 528/2012
Biocidal Products Regulation (EU) No 528/2012 of the European Parliament and of the Council of 22 May 2012 concerning the making available on the market and use of biocidal products (current consolidated version: 2021-06)

2000/532/EC
Commission decision dated 3 May 2000 replacing decision 94/3/EC on a waste directory in accordance with Article 1 a) of Council Directive 75/442/EEC on waste and Council decision 94/904/EC on a directory of hazardous waste in terms of Article 1, paragraph 4 of Directive 91/689/EEC on hazardous waste

Belgian Royal Decree C-2014/24239
Belgisch Staatsblad 8 MEI 2014, p. 60603. — Koninklijk besluit tot vaststelling van de drempelniveaus voor de emissies naar het binnenmilieu van bouwproducten voor bepaalde geoogde gebruiken

Blue Angel
Environmental label organised by the federal government of Germany www.blauer-engel.de

Candidate list
Candidate List of substances of very high concern for Authorisation, published in accordance with Article 59(10) of the REACH Regulation, ECHA, www.echa.europa.eu/candidate-list-table

CPR
CPR Regulation (EU) No 305/2011 of the European Parliament and of the Council of 9 March 2011 laying down harmonised conditions for the marketing of construction products and repealing Council Directive 89/106/EEC

Decopaint Directive
Directive 2004/42/CE of the European Parliament and the council of 21 April 2004 on the limitation of emissions of volatile organic compounds due to the use of organic solvents in certain paints and varnishes and vehicle refinishing products and amending Directive 1999/13/EC

EMICODE
EMICODE, GEV – Gemeinschaft Emissionskontrollierte Verlegewerkstoffe, Klebstoffe und Bauprodukte e. V. (pub.).www.emicode.de

GaBi 10 software & documentation
Data base for Life Cycle Engineering LBP, University of Stuttgart and Sphera, documentation of GaBi 10 data sets http://documentation.gabi-software.com/, 2020

German AgBB
Committee for Health-related Evaluation of Building Products: health-related evaluation of emissions of volatile organic compounds (VOC and SVOC) from building products; status: June 2012 www.umweltbundesamt.de/produkte/bauprodukte/agbb.htm

IBU 2021
Institut Bauen und Umwelt e.V.: General Instructions for the EPD programme of Institut Bauen und Umwelt e.V. EPD programme. Version 2.0. Berlin: Institut Bauen und Umwelt e.V., 2021
www.ibu-epd.com

Indoor Air Comfort
Product certification by Eurofins, Hamburg, Germany www.eurofins.com .

PCR Part A
Product Category Rules for Building-Related Products and Services, Part A: Calculation Rules for the Life Cycle Assessment and Requirements on the Project report, Version 1.1, Institut Bauen und Umwelt e.V., 2021-01

PCR Part B
Product Category Rules for Construction Products. Part B: Dispersion adhesives and primers for floor coverings, Version 1.7, 2019.

REACH
Directive (EG) No. 1907/2006 of the European Parliament and of the Council dated 18 December 2006 on the registration, evaluation, approval and restriction of chemical substances (REACH), for establishing a European Agency for chemical substances, for amending Directive 1999/45/EC and for annulment of Directive (EEC) No. 793/93 of the Council, Directive (EC) No. 1488/94 of the Commission, Guideline 76/769/EEC of the Council and Guidelines 91/155/EEC, 93/67/EEC, 93/105/EC and 2000/21/EC of the Commission.

Publisher
Institut Bauen und Umwelt e.V.
Hegelplatz 1
10117 Berlin
Germany

Tel +49 (0)30 3087748- 0
Fax +49 (0)30 3087748- 29
Mail info@ibu-epd.com
Web **www.ibu-epd.com**

Programme holder
Institut Bauen und Umwelt e.V.
Hegelplatz 1
10117 Berlin
Germany

Tel +49 (0)30 - 3087748- 0
Fax +49 (0)30 – 3087748 - 29
Mail info@ibu-epd.com
Web **www.ibu-epd.com**

Author of the Life Cycle Assessment
Sphera Solutions GmbH
Hauptstraße 111- 113
70771 Leinfelden-Echterdingen
Germany

Tel +49 711 341817-0
Fax +49 711 341817-25
Mail info@sphera.com
Web **www.sphera.com**

Owner of the Declaration
FEICA - Association of the European Adhesive and Sealant Industry
Rue Belliard 40 box 10
1040 Brussels
Belgium

Tel +32 (0)267 673 20
Fax +32 (0)267 673 99
Mail info@feica.eu
Web **www.feica.eu**

EFCC - European Federation for Construction Chemicals
Boulevard du Triomphe 172
1160 Brussels
Belgium

Tel +32289720-39
Fax +32289720-37
Mail info@efcc.be
Web **www.efcc.eu**

Industrieverband Klebstoffe e.V
Völklinger Straße 4
40219 Düsseldorf
Germany

Tel +49 (0)211 67931-10
Fax +49 (0)211 67931-33
Mail info@klebstoffe.com
Web **www.klebstoffe.com**

Deutsche Bauchemie e.V.
Mainzer Landstr. 55
60329 Frankfurt
Germany

Tel +49 (0)69 2556-1318
Fax +49 (0)69 2556-1319
Mail info@deutsche-bauchemie.de
Web **www.deutsche-bauchemie.de**